

LAW OFFICES

SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC

2100 PENNSYLVANIA AVENUE, N.W.

WASHINGTON, D.C. 20037-3202

TELEPHONE (202) 293-7060

FACSIMILE (202) 293-7860

July 16, 1998

SENIOR COUNSEL

RICHARD C. SUGHRUE, P.C.

DONALD E. ZINN

ROBERT G. MCMORROW, P.C.

JAPAN OFFICE

TOEI NISHI SHIMBASHI BLDG. 4F

13-5 NISHI SHIMBASHI 1-CHOME

MINATO-KU, TOKYO 105, JAPAN

TELEPHONE (03) 3503-3760

FACSIMILE (03) 3503-3756

CALIFORNIA OFFICE

1010 EL CAMINO REAL

MENLO PARK, CA 94025

TELEPHONE (650) 325-5800

FACSIMILE (650) 325-6606

jc518 U.S. PTO
09/116589
07/16/98

GEORGE F. LEHNIGK
MARIE-CLAIRE BOISVERT MAPLE
DEAN H. NAKAMURA, Ph.D.*
JOHN T. CALLAHAN
MARY E. GOULET
PETER A. MCKENNA
ANIRMA RAKSHAPAL GUPTA
STEVEN M. GRUSKIN
LAURA C. BRUTMAN
JOHN F. RABENA
GRANT K. ROWAN
KEVIN A. WOLFF
OLIVER R. ASHE, JR.*
SUSAN PERNG PAN
EDWARD F. KENEHAN, JR.
JEAN C. EDWARDS
AMY L. MILLER*
J. WARREN LYTLE, JR.
KEVIN L. PONTIUS*
REBECCA A. GOLDMAN*
LEE C. WRIGHT*
STAN TORGOVITSKY*
CARL J. PELLEGRINI*
PHILIP I. DATLOW*
KELLY G. HYNDMAN*
ELLEN M. RESNICK*
RAJA N. SALIBA*
RAY HEFLIN*
CHID SUBRAMANIAN*
PATRICK B. LAW
JEFFREY A. SCHMIDT*
KEVIN J. STEIN*
KRISTINA M. JAHNS*

*ADMITTED OTHER THAN D.C.

BOX PATENT APPLICATION

Assistant Commissioner for Patents

Washington, D.C. 20231

Re: Application of **Shingo NISHIKAWA, Kenji UEDA, Toshikazu SEGAWA, Tsuyoshi HOTTA, Yuko KUWABARA and Masachika WATANABE**

REFLECTION TYPE DIFFUSE HOLOGRAM, HOLOGRAM FOR REFLECTION HOLOGRAM COLOR FILTERS, ETC., AND REFLECTION TYPE DISPLAY DEVICE USING SUCH HOLOGRAMS

Our Ref: Q51098

Dear Sir:

This is a request for a Continuation-In-Part Application of pending prior Application No. 08/839,666 filed April 14, 1997 of Shingo NISHIKAWA, Kenji UEDA, Toshikazu SEGAWA, Tsuyoshi HOTTA, Yuko KUWABARA and Masachika WATANABE entitled REFLECTION TYPE DIFFUSE HOLOGRAM, HOLOGRAM FOR REFLECTION HOLOGRAM COLOR FILTERS, ETC., AND REFLECTION TYPE DISPLAY DEVICE USING SUCH HOLOGRAMS.

Attached hereto is the Continuation-In-Part Application including the specification, abstract, claims and 32 sheets of formal drawings.

The executed Declaration and Power of Attorney and Assignment will be submitted at a later date.

Amend the specification by inserting before the first line the sentence: --This is a Continuation-in-Part of Application No. 08/839,666 filed April 15, 1997.--

Assistant Commissioner
for Patents

Page 2

The Government filing fee is calculated as follows:

Total claims	<u>80</u> - 20 = <u>60</u>	x \$22 =	<u>\$1,320.00</u>
Independent claims	<u>19</u> - 3 = <u>16</u>	x \$82 =	<u>\$1,312.00</u>
Base Fee			\$ <u>790.00</u>
Multiple Dependent Claim Fee			
(\$270.00/135.00)			\$ <u>270.00</u>
TOTAL FILING FEE			\$3,692.00
Recordation of Assignment			\$ <u>00.00</u>
TOTAL FEE			\$3,692.00

Please charge the statutory filing fee of \$3,692.00 to Deposit Account No. 19-4880. You are also directed and authorized to charge or credit any difference or overpayment to Deposit Account No. 19-4880. The Commissioner is hereby authorized to charge any fees under 37 C.F.R. §§ 1.16 and 1.17 and any petitions for extension of time under 37 C.F.R. § 1.136 which may be required during the entire pendency of the application to Deposit Account No. 19-4880. A duplicate copy of this transmittal letter is attached.

Priority is claimed from Japanese Application No. 092518/1996, filed April 15, 1996, Japanese Application 123390/1996, filed May 17, 1996, Japanese Application 192020/1996, filed July 22, 1996, Japanese Application 197574/1996, filed July 26, 1996 and Japanese Application No. 237857/1996, filed September 9, 1996. The priority documents were filed in parent Application No. 08/839,666.

Priority is also claimed from Japanese Application No. 9-190970, filed July 16, 1997, which will be submitted at a later date.

Respectfully submitted,

SUGHRUE, MION, ZINN,
MACPEAK & SEAS, PLLC
Attorneys for Applicant

By:



Peter A. McKenna

Registration No. 38,551

TITLE OF THE INVENTION

REFLECTION TYPE DIFFUSE HOLOGRAM, HOLOGRAM FOR REFLECTION
HOLOGRAM COLOR FILTERS, ETC., AND REFLECTION TYPE DISPLAY
5 DEVICE USING SUCH HOLOGRAMS

BACKGROUND OF THE INVENTION

The present invention relates to a reflection type
diffuse hologram that can be used for display devices such as
10 liquid crystal display devices, a hologram for reflection
hologram color filters, etc., and a reflection type display
device using such holograms.

Backlight used with a liquid crystal display device
should have some scattering characteristics, so that the
15 display device can have a wide viewing angle. So far,
scattering characteristics have been imparted to backlight by
use of beads or the like, but a problem with this is that too
large an angle of diffusion results in wasteful illumination
light loss.

20 This is also true of an automotive brake lamp or
direction indicator. That is, although too large a diffusion
angle is not required in view of the positional relation to
succeeding cars, light from these lamps is not only
wastefully consumed but also becomes dark because lenses
25 positioned in front of the lamps cause the light to be
diffused at an angle larger than required.

The present applicant has filed Japanese Patent
Application No. 12170/1993 to come up with a color filter in
which a hologram is used to achieve a remarkable increase in

09116584.071649

the efficiency of backlight used for liquid crystal display purposes, etc., and a liquid crystal display device that makes use of such a color filter.

A typical liquid crystal display device that makes use
5 of this hologram color filter will now be briefly described
with reference to a sectional view attached hereto as Figure
43. As illustrated, a hologram array 55 forming the color
filter is spaced away from the side of a liquid crystal
display element 56 upon which backlight 53 is to strike, said
10 element being regularly divided into liquid crystal cells 56'
(pixels). On the back side of the liquid crystal display
element 56 and between the liquid crystal cells 56' there are
located black matrices 54. Although not illustrated,
polarizing plates are arranged on the incident side of the
15 hologram array 55, and the exit side of the liquid crystal
display element 56. As is the case with a conventional color
liquid crystal display device, between the black matrices 54
there may additionally be located an absorption type of color
filters which transmit light rays of colors corresponding to
20 pixels R, G, and B.

The hologram array 55 comprises micro-holograms 55'
which are arranged in an array form at the same pitch as that
of R, G, and B spectral pixels, corresponding to the period
of repetition of R, G, and B spectral pixels, i.e., sets of
25 liquid crystal cells 56', each including three adjoining
liquid crystal cells 56' of the liquid crystal display
element 6 as viewed in a plane direction of the drawing
sheet. One micro-hologram 55' is located in line with each

set of three adjoining liquid crystal cells 56' of the liquid crystal display element 6 as viewed in the plane direction of the drawing sheet. The micro-holograms 55' are then arranged in a Fresnel zone plate form such that a green component ray of the backlight 3 incident on the hologram array 55 at an angle θ with respect to its normal line is collected at a middle liquid crystal cell G of the three R, G, and B spectral pixels corresponding to each micro-hologram 55'. Each of the micro-hologram 55' in this case is constructed from a relief, phase, amplitude or other transmission type of hologram which has little, if any, dependence of diffraction efficiency on wavelength. The wording "little, if any, dependence of diffraction efficiency on wavelength" used herein is understood to refer specifically to a hologram of the type which diffracts all wavelengths by one diffraction grating, much unlike a Lippmann type hologram which diffracts a particular wavelength alone but does not substantially permit other wavelengths to be transmitted therethrough. The diffraction grating having little dependence of diffraction efficiency on wavelength diffracts different wavelengths at different angles of diffraction.

In such an arrangement, consider now the incidence of the white backlight 3 from the side of the hologram array 55, which does not face the liquid crystal display element 56 at the angle θ with respect to its normal line. The angle of diffraction of the light by the micro-hologram 55' varies depending on wavelength, so that light collection positions for wavelengths are dispersed in a direction substantially

parallel with the surface of the hologram array 55. If the
hologram array 55 is constructed and arranged such that the
red wavelength component is diffractively collected at a red-
representing liquid crystal cell R; the green wavelength
5 component at a green-representing liquid crystal cell G; and
the blue wavelength component at a blue-representing liquid
crystal cell B, the color components pass through the
corresponding liquid crystal cells 56' with no or little
attenuation through the black matrices 4, so that color
10 displays can be presented depending on the state of the
liquid crystal cells 56' at the corresponding positions. It
is here noted that the angle of incidence θ of backlight 53 on
the hologram array 55 is determined by various conditions
including hologram-recording conditions, the thickness of
15 hologram array 55, and the distance between the hologram
array 55 and the liquid crystal display element 6.

By using the hologram array 55 as a color filter in this
way, the wavelength components of backlight used with a
conventional color filter are allowed to strike on the liquid
20 crystal cells 56' without extravagant absorption, so that the
efficiency of utilization thereof can be greatly improved.

The aforesaid hologram color filter proposed by the
present applicant is applicable to only a color liquid
crystal display device making use of backlight. However,
25 when surrounding ambient light alone is used as illumination
light, this hologram color filter cannot diffract, and
collect its wavelength components into desired positions. In
other words, this hologram color filter can never be applied

to a direct-view type of liquid crystal display device or other like device in which surrounding ambient light is used as illumination light, or any particular backlight source is not required.

- 5 Moreover, the applicant has filed Japanese Patent Application No. 120016/1993 to come up with a method for using a swelling film to make from a volume hologram having uniform interference fringes recorded therein a color pattern that varies in reconstructed color depending on position.
- 10 The principles are similar to those applied to a photopolymer. First, a swelling film is prepared by mixing a monomer or oligomer, a photopolymerization initiator, etc. with a binder polymer. Then, the swelling film is irradiated with a given quantity of light before or after its close
- 15 contact with a photopolymer or other photosensitive material having interference fringes recorded therein, so that a given proportion of the monomer or oligomer contained in the swelling film, on the one hand, is polymerized for deactivation and the amount of the remaining active monomer
- 20 or oligomer, on the other hand, is controlled. The thus controlled amount of the monomer or oligomer is diffused, and swollen into the photosensitive material with interference fringes recorded therein, whereby fringe spacings are precisely controlled to any desired quantity to control
- 25 reconstruction wavelengths to given ones. After this swelling treatment, the photosensitive material with the interference fringe recorded therein is irradiated with light or otherwise heated to fix the diffused monomer or oligomer

094433 07433

in the interference fringes, so that there can be obtained a
hologram excelling in the storage stability of reconstructed
colors. In addition, a color pattern can be formed on the
hologram by allowing the illumination light to have a spatial
5 distribution.

This method will now be explained in a little more
detail with reference to Figures 44 and 45. Figure 44
illustrates the principles applied when the swelling agent
(monomer or oligomer) contained in the swelling film is
10 deactivated by irradiation with light after the swelling film
has been brought into close contact with the photosensitive
material, and Figure 45 depicts the principles applied when
the swelling agent contained in the swelling film is
deactivated by irradiation with light before the swelling
15 film is brought into close contact with the photosensitive
material. Referring to Figure 44(a), such a volume hologram
64 as depicted in Figure 44(b) is obtained by striking object
light 62 and reference light 63 on both sides of a photo-
polymer or other photosensitive material 61 to record an
20 interference fringe therein. As depicted in Figure 44(c), a
swelling film 65 prepared by mixing a monomer or oligomer, a
photopolymerization initiator, etc. with a binder polymer is
then brought into close contact with the photosensitive
material. Subsequently, either the hologram 64 or the
25 swelling film 65 is irradiated with light 66, as depicted in
Figures 44(d1) to (d3), before or at the same time as heating
is carried out to increase the degree of diffusion of the
penetrating monomer or oligomer in the swelling film 65.

SECRET

This irradiation with light 66 causes a part or all of the penetrating active monomer or oligomer in the swelling film 65 to be polymerized, and so deactivated, at a proportion corresponding to the quantity of irradiating light 66, so that the ability of the monomer or oligomer to penetrate (diffuse) vanishes substantially. When the quantity of irradiating light 66 is large (Figure 44(d1)), therefore, nearly all of the penetrating active monomer or oligomer in the swelling film 65 is deactivated, so that the monomer or oligomer does not substantially penetrate into the hologram 64 even upon heated. If, for instance, interference fringes are recorded in the volume hologram 64 with a blue wavelength in Figure 44(a), the hologram 64 subject to the swelling step in Figure 44(d1) does not substantially swell, and diffracts and reconstructs blue light. When the quantity of irradiating light 66 is moderate (Figure 44(d2)), on the other hand, about a half of the penetrating active monomer or oligomer in the swelling film 65 is deactivated. Another half of the penetrating monomer or oligomer penetrates into the hologram 64 upon heated, which in turn swells moderately. For this reason, the hologram 64 subject to the swelling step shown in Figure 44(d2) diffracts, and reconstructs green light that is longer in wavelength than blue light. Moreover, when the swelling film is not irradiated with light 66 (Figure 44(d3)), nearly all of the penetrating monomer or oligomer from the swelling film 65 penetrates into the hologram 64, which in turn swells to the maximum extent. For this reason, the hologram 64 subject to the swelling step

shown in Figure 44(d3) diffracts, and reconstructs red light that is longer in wavelength than green light. By controlling the quantity of light 66 with which the swelling film 65 into close contact with the hologram 64 is

5 irradiated, it is thus possible to optionally regulate the color to be reconstructed to one lying between red and blue.

Referring then to Figure 45, especially Figures. 45(a) and 45(b), a volume hologram 64 is obtained as depicted in Figures 44(a) and (b). As shown in Figures 45(c1) through
10 (c3), a swelling film 65 is prepared by mixing a monomer or oligomer, a photo-polymerization initiator, etc. with a binder polymer. Upon this film irradiated with a given quantity of light 66, a part or all of the penetrating active monomer or oligomer contained therein is deactivated at a
15 proportion corresponding to the quantity of light 66, so that the ability of the monomer or oligomer to penetrate (diffuse) vanishes. When the swelling film 65 already irradiated with light 66 is brought into close contact with the hologram 64, as depicted in Figures 45(d1) through 45(d3), and then heated
20 as shown in Figure 44, the degree of swelling of the hologram 64 varies depending on the quantity of light 66. By controlling the quantity of light 66 with which the swelling film 65 is irradiated, it is thus possible to optionally regulate the color to be reconstructed to one lying between
25 red and blue.

In this regard, it is noted that the swelling film 65 is prepared by mixing a monomer or oligomer, a photo-polymerization initiator, etc. with a binder polymer, and so

0916389-071690

is similar to a photopolymer used for recording holograms. Therefore, the hologram-recording photopolymer may be used as the swelling film 65; that is, it is unnecessary to prepare any special swelling film.

5 The aforesaid color pattern-making method proposed by the present applicant is to control the quantity of light with which the swelling film is irradiated before or after it is brought into close contact with a photosensitive material having interference fringes already recorded therein, thereby
10 controlling the amount of the active monomer or oligomer contained in the swelling film, so that the proportion of swelling of the interference fringes (or the interference fringe spacings) can be controlled to regulate the color to be reconstructed to a given one. In short, the color to be
15 reconstructed is controlled by the quantity of irradiating light.

However, one problem with the aforesaid method is that it is not always easy to precisely control the quantity of light to develop a given color, and another possible problem
20 is that the reproducibility of the color reconstructed is not stable.

SUMMARY OF THE INVENTION

In view of such problems associated with the prior art, it is an object of the present invention to provide a
25 diffusing plate which can use a hologram to limit the angle of diffusion within a desired range, and makes bright display, etc. possible.

Another object of the present invention is to provide a reflection type of direct-view color display device such as a color liquid crystal display device, which makes use of a hologram color filter already proposed by the present
5 applicant but makes no use of any backlight source at all.

Yet another object of the present invention is to provide a reflection type color display device such as a color liquid crystal display device, which uses a hologram reflection layer as a color filter but makes no use of any
10 backlight source.

Still yet another object of the present invention is to provide a hologram recording medium, and a hologram color display medium, which can all be utilized as a color filter of a reflection type color display device, and a method of
15 making them.

According to the present invention, the objects mentioned above can be achieved by the provision of a reflection type diffuse hologram characterized by reflecting, and diffracting light incident thereon at an angle with
20 respect to a normal direction while it is diffused within a desired angle range. Throughout the specification, it is to be noted that the angle of incident light with respect to the normal direction may include 0° , or the angle of incidence may be 0° .

25 In this case, it is desired that the angle of diffusion lie within a range of 10° to 35° .

Another reflection type diffuse hologram of the present invention is characterized by having been formed by allowing

094639-074639

diffused light that diffuses within a desired angle range, and parallel light to strike on both sides of a volume hologram-recording photosensitive material, and interfere therein.

5 It is here to be noted that an image has simultaneously been recorded in the reflection type diffuse hologram of the present invention in a reconstructible fashion.

 It is also to be noted that the reflection type diffuse hologram may be located on a backlight side of a liquid
10 crystal display device for diffuse illumination purposes.

 The present invention provides a method for fabricating a reflection type diffuse hologram characterized in that a transmission type diffusing plate having a diffusion angle characteristic within a desired angle range is located in
15 close contact with, or in proximity to, a volume hologram-recording photosensitive material, and two light beams are allowed to strike on front and back sides of the combined diffusing plate and photosensitive material for interference recording.

20 In this case, the transmission type diffusing plate used may be a diffusing plate of a 20% to 60% haze, an array of microlenses, a lenticular screen or the like.

 A reflection type of direct-view color display device using a hologram color filter according to the present
25 invention - which is provided to achieve the objects mentioned above - comprises a hologram color filter composed of an array of element light-collecting holograms,

0011589-0150

each of said element light-collecting holograms comprising a hologram color filter for subjecting white light incident at a given angle with respect to a normal line of a hologram-recorded surface to wavelength dispersion in a direction substantially along said hologram-recorded surface for spectral diffraction, a reflection type hologram located in the vicinity of a light-collection surface thereof, and a transmission type spatial light modulator located between said hologram color filter and said reflection type hologram.

In this case, it is preferable that the reflection type hologram has interference fringes recorded in the vicinity of a position on which white light strikes while said white light is separated into each spectral component of each color, said interference fringes reflecting light of wavelength of each color in an identical direction.

The reflection type hologram may be of diffusibility.

For the transmission type spatial light modulator, for instance, a liquid crystal display element may be used.

A reflection type color display device of the present invention - which is provided to achieve the aforesaid object - is characterized by comprising a transmission type spatial light modulator comprising a collection of pixels, and having a controllable transmittance per pixel, and a reflection type hologram color filter located on a back side of said modulator.

In this case, it is preferable that the reflection type hologram color filter comprises periodically arranged volume hologram elements varying in reflection, and diffraction

wavelength for each position of the pixels in the transmission type spatial light modulator.

In this connection, the reflection type hologram color filter may be of diffusibility.

5 It is preferable that the reflection type hologram color filter has an absorption layer located on a back side thereof.

Also, the reflection type hologram color filter may be provided on its back side with an absorption type color
10 filter, which is provided on its back side with a backlight source, so that color information is interchangeable when said backlight source is turned on, said color information being displayed on each pixel in the transmission type spatial light modulator.

15 It is here noted that for the transmission type spatial light modulator, for instance, a liquid crystal display element, a polymer-dispersed type liquid crystal display element or the like may be used.

A hologram-recorded medium of the present invention -
20 which is provided to achieve the aforesaid object - is an imagewise or other pattern-recorded medium comprising a collection of pixels, characterized in that any one of a plurality of volume type diffraction gratings comprising volume holograms and differing from each other is assigned to
25 at least a part of said pixels.

In this case, it is preferable that a plurality of volume type diffraction gratings comprising volume holograms and differing from each other include at least three volume

type diffraction gratings which are identical in orientation of grating surface with each other but different in grating spacing from each other.

It is also preferable that at least two of a plurality
5 of mutually different volume type diffraction gratings are multi-recorded in at least a part of the pixels.

It is further preferable that a volume type diffraction grating that expresses red, a volume type diffraction grating that expresses green, and a volume type diffraction grating
10 that expresses blue are assigned to three dot areas into which at least a part of the pixels is divided, or to three adjoining pixels, so that color tone or gradation is controlled by varying a dot percent occupied by said volume type diffraction gratings, or a diffraction efficiency ratio
15 between said volume type diffraction gratings.

The hologram-recorded medium of the present invention may have a reflecting layer on its back side.

Each of pixels in the hologram-recorded medium of the present invention may be of diffusibility.

20 The hologram-recorded medium of the present invention as mentioned above may be used as a reflection type hologram color filter.

Such a hologram-recorded medium of the present invention is fabricated as recited below.

25 (1) A method of fabricating a hologram-recorded medium characterized by stacking a volume hologram photosensitive material on a reflection type relief hologram, and striking reconstructing illumination light of given wavelength on said

2025 RELEASE UNDER E.O. 14176

reflection type relief hologram through said volume hologram
photosensitive material, so that interference fringes
produced by interference of light diffracted from said
reflection type relief hologram and the incident light are
5 recorded in said volume hologram photosensitive material.

(2) A method of fabricating a hologram-recorded medium
characterized by stacking a volume hologram photosensitive
material on a transmission type hologram, and striking
reconstructing illumination light of given wavelength on a
10 side of said transmission type hologram that is not opposite
to said volume hologram photosensitive material, so that
interference fringes produced by interference of light
diffracted from said transmission type hologram and reference
light incident on said volume hologram photosensitive
15 material are recorded in said volume hologram photosensitive
material.

(3) A method of fabricating a hologram-recorded medium
characterized by stacking a volume hologram photosensitive
material on a transmission type hologram, and striking
20 reconstructing illumination light of given wavelength on a
side of said transmission type hologram that is not opposite
to said volume hologram photosensitive material, so that
interference fringes produced by interference of light
diffracted from said transmission type hologram and zero-
25 order transmitted light are recorded in said volume hologram
photosensitive material, followed by provision of a
reflecting layer on a back side of said volume hologram
photosensitive material.

(4) A method of fabricating a hologram-recorded medium characterized by locating a mask plate having an opening pattern on one side of a volume hologram photosensitive material and a reflecting mirror on another side of said volume hologram photosensitive material, said reflecting mirror having a specific angle of inclination with respect to said volume hologram photosensitive material, and striking a light beam on said volume hologram photosensitive material through said opening pattern in said mask plate, so that interference fringes produced by interference of the incident light and light reflected from said reflecting mirror are recorded in said volume hologram photosensitive material.

(5) A method of fabricating a hologram-recorded medium characterized by locating a mask plate having an opening pattern on one side of a volume hologram photosensitive material and an off-axis reflection type hologram on another side of said volume hologram photosensitive material, said off-axis reflection type hologram diffracting a light beam incident at a given angle of incidence in an opposite direction at a specific angle with respect thereto, and striking a light beam on said volume hologram photosensitive material through said opening pattern in said mask plate, so that interference fringes produced by interference of the incident light and light diffracted from said off-axis reflection type hologram are recorded in said volume hologram photosensitive material.

(6) A method of fabricating a hologram-recorded medium characterized by locating a composite reflector comprising a

collection of micro-mirror surfaces varying in reflection direction per position on a back side of a volume hologram photosensitive material, and striking a light beam on a surface side of said volume hologram photosensitive material, so that interference fringes produced by interference of the incident light and light reflected from said composite reflector are recorded in said volume hologram photosensitive material.

(7) A method of fabricating a hologram-recorded medium characterized by striking two coherent thin light beams at a position of each of pixels in a volume hologram photosensitive material while said beams intersect at a relative angle corresponding to said position, thereby recording in said volume hologram photosensitive material interference fringes having an inclination and a pitch depending on said pixel position.

The hologram color display medium of the present invention - which is provided to achieve the aforesaid objection - is a hologram color display medium having interference fringes of light recorded in a thickness direction of a film, characterized by using two swelling films each containing a penetrating monomer or oligomer that is diffusible externally from a surface of said film, said penetrating monomer or oligomer being deactivated according to a given deactivation pattern, so that said hologram is swollen by said penetrating monomer or oligomer diffused from both surfaces of said hologram at different degrees of swelling depending on position.

In this case, it is preferable that the aforesaid two swelling films are brought into close contact with both surfaces of the aforesaid hologram, so that a two-dimensional diffraction pattern of two or more colors is obtained by the combination of a deactivation pattern of one swelling film with that of another swelling film.

A color image may be expressed by means of a collection of color display micro-units, each comprising a combination of two or more micro-pixels displaying two or more different colors, and the dot percent of dots in each color display micro-unit may be varied to express each color display micro-unit in any desired color by additive color mixing. If, in this case, the interference fringes recorded in the hologram is designed such that diffraction efficiency changes depending on the positions of the color display micro-units, or the hologram itself or its diffraction-side surface is designed such that absorptance changes depending on the positions of the color display micro-units, it is then possible to control the brightness or luminance of each color display micro-unit.

It is preferable that the hologram is a volume phase type hologram, and it is then preferable that the hologram is a hologram recorded in a photopolymer.

Also, the hologram color display medium of the present invention may be of diffusibility.

Such a hologram color display medium of the present invention as mentioned above may be used in the form of a reflection type hologram color filter.

Further, the present invention provides a first method of fabricating a hologram color display medium including a hologram having interference fringes of light recorded in a thickness direction of a film, wherein two swelling films each containing a penetrating monomer or oligomer that is diffusible externally from a surface of said film, said penetrating monomer or oligomer being deactivated according to a given deactivation pattern, are used so that said hologram is swollen by said penetrating monomer or oligomer diffused from both surfaces of said hologram at different degrees of swelling depending on position, characterized in that before or after the close contact of the two swelling films, in which the penetrating monomer or oligomer contained in that position is deactivated by irradiation of a given or more quantity of light, with both surfaces of said hologram, said two swelling films are irradiated according to said given deactivation pattern with a given or more quantity of light, and said hologram with the thus deactivated swelling films brought into close contact with both surfaces thereof is heated, thereby diffusing said penetrating monomer or oligomer from active areas of said swelling films into said hologram.

Furthermore, the present invention provides a second method of fabricating a hologram color display medium including hologram having interference fringes of light recorded in a thickness direction of a film, wherein two swelling films each containing a penetrating monomer or oligomer that is diffusible externally from a surface of said

film, said penetrating monomer or oligomer being deactivated according to a given deactivation pattern, are used so that said hologram is swollen by said penetrating monomer or oligomer diffused from both surfaces of said hologram at

5 different degrees of swelling depending on position, characterized in that before or after the close contact of one swelling film, in which the penetrating monomer or oligomer contained in that position is deactivated by irradiation of a given or more quantity of light, with one

10 surface of said hologram, said one swelling film is irradiated according to said given deactivation pattern with a given or more quantity of light; said hologram with the thus deactivated swelling film brought into close contact with said one surface is heated, thereby diffusing said

15 penetrating monomer or oligomer from an active area of said one swelling film into said hologram; before or after the close contact of another swelling film, in which the penetrating monomer or oligomer contained in that position is deactivated by irradiation of a given or more quantity of

20 light, with another surface of said hologram, said another swelling film is irradiated according to said given deactivation pattern with a given or more quantity of light; said hologram with the thus deactivated swelling film brought into close contact with said another surface is again heated,

25 thereby diffusing said penetrating monomer or oligomer from an active area of said another swelling film into said hologram.

0946390469

In these methods, it is preferable that the hologram is a volume phase type hologram, and it is then preferable that the hologram is a hologram recorded in a photopolymer.

Furthermore, the present invention provides another multicolor hologram display unit comprising volume holograms multi-recorded therein, said volume holograms diffracting light of at least two different wavelengths, characterized by further comprising a color tuning film containing a penetrating monomer or oligomer that is diffusible from a surface thereof to an outside thereof, said penetrating monomer or oligomer being deactivated according to a given deactivation pattern, so that said monomer or oligomer is diffused from said color tuning film, whereby a portion of said volume holograms in no alignment with said deactivated pattern is swollen to diffract light of a wavelength that is different from a wavelength that is diffracted by a portion of said volume holograms in alignment with said deactivated pattern.

Preferably, the multi-recorded volume holograms are
20 recorded all over a surface thereof, while the deactivation
pattern comprising dots. This multicolor volume hologram
display unit may be used as a hologram reflecting and
scattering plate for liquid crystal display apparatus. The
multicolor volume hologram display unit may also include an
25 area having a different dot percent.

Preferably, the multi-recorded volume holograms are each recorded in a separate pattern area. In this case, an area swollen by the color tuning film and an unswollen area

provide dots wherein red, green, and blue colors are reconstructible. The multicolor volume hologram display unit may also include an area having a different dot area.

The color tuning film may be integrally provided on the
5 multicolor hologram display unit.

It is to be noted that the foregoing multicolor hologram display unit of the invention may be used as a reflection type hologram color filter.

Still other objects and advantages of the invention will
10 in part be obvious and will in part be apparent from the specification.

The invention accordingly comprises the features of construction, combinations of elements, and arrangement of parts which will be exemplified in the construction herein-
15 after set forth, and the scope of the invention will be indicated in the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 illustrates a typical arrangement of how to
20 record a reflection type diffuse hologram according to the invention.

Figure 2 is a schematic which shows that the reflection type diffuse hologram depicted in Figure 1 has the ability to diffuse.

25 Figure 3 provides an illustration of how the reflection type diffuse hologram of the invention is located for a brake lamp or direction indicator lamp, and what effect is obtained in this case.

Figure 4 provides an illustration of how the reflection type diffuse hologram of the invention is located for

009720" 6899760

backlighting a liquid crystal display device, and what effect is obtained in this case.

Figure 5 illustrates a typical arrangement of how to record a reflection type diffuse hologram using an array of microlenses or a lenticular screen in place of a diffusing plate.

Figure 6 provides an illustration of how to make an exemplary reflection type diffuse hologram of the invention.

Figure 7 is a graph of how the angle of diffusion of a reflection type diffuse hologram changes as the haze of a diffusing plate changes.

Figure 8 is a sectional schematic showing one embodiment of a reflection type of direct-view color display device using a hologram color filter of the invention.

Figure 9 is an exploded perspective schematic of one embodiment of a reflection type color display device of the invention.

Figure 10 provides an illustration of how to record a volume type reflection hologram, and the action of this volume reflection hologram.

Figure 11 is a schematic illustrating the construction, and action of a reflection type hologram color filter used in the invention.

Figure 12 is a sectional schematic of one modification of the display device depicted in Figure 9, which is designed so that color information can be displayed even by backlight illumination.

Figure 13 provides illustrations of how hologram elements of a reflection type hologram color filter are two-dimensionally arranged.

Figure 14 provides illustrations of an exemplary construction of a hologram-recording medium according to the invention.

Figure 15 is schematics for illustrating one area gradation method for changing color tone by dot percent changes.

Figure 16 is schematics for illustrating another area gradation method for changing color tone by dot percent changes.

Figure 17 is schematics for illustrating a density gradation method for controlling color tone, and gradation by placing the efficiency of diffraction of interference fringes under control.

Figure 18 illustrates how to make a hologram-recorded medium from a computer-generated hologram by replication.

Figure 19 is a sectional schematic of a typical hologram-recorded medium made using a transmission type computer-generated hologram.

Figure 20 illustrates how to fabricate a hologram-recorded medium using a mask pattern, and an inclined plane mirror.

Figure 21 illustrates how to fabricate a hologram-recorded medium using a mask pattern, and an off-axis reflection type hologram.

2025 RELEASE UNDER E.O. 14176

Figure 22 illustrates how to fabricate a hologram-recorded medium using a group of micro-mirrors that vary in reflection direction per position.

Figure 23 illustrates how to fabricate a hologram-recorded medium while two coherent light beams are moved relatively with respect to the hologram-recording medium.

Figure 24 illustrates the first principle of the method for fabricating a hologram color display medium of the invention.

Figure 25 illustrates the second principle of the method for fabricating a hologram color display medium of the invention.

Figure 26 is a graph showing a diffraction efficiency profile of a first embodiment of the volume hologram of the invention.

Figure 27 is a graph showing a diffraction efficiency profile of a second embodiment of the volume hologram.

Figure 28 is a plan schematic of one embodiment of the multicolor hologram display unit of the invention.

Figure 29 is a plan schematic of one mask pattern used in the process of fabricating the multicolor hologram display unit of Fig. 28.

Fig. 30 a plan schematic of another mask pattern used in the process of fabricating the multicolor hologram display unit of Fig. 28.

Figure 31 is illustrative of the step of deactivating a part of the recording photosensitive material used in the

process of fabricating the multicolor hologram display unit of Fig. 28.

Figure 32 is illustrative of the step of recording a hologram in the recording photosensitive material in the process of fabricating the multicolor hologram display unit of Fig. 28.

Figure 33 is illustrative of the step of replicating the multicolor hologram display unit of Fig. 28 from an original plate.

Figure 34 is illustrates of the state of each area in the multicolor hologram display unit of Fig. 28.

Figure 35 is illustrative of on what principle the multicolor hologram display unit of Fig. 28 produces a halftone color.

Figure 36 is illustrative of a part of the process of recording another embodiment of the multicolor hologram display unit of the invention.

Figure 37 is illustrative of another part of the process of recording another embodiment of the multicolor hologram display unit of the invention.

Figure 38 is illustrative of an example of the diffraction efficiency profile of the multicolor display unit shown in Figs. 36 and 37.

Figure 39 is a sectional schematic of a liquid crystal display apparatus constructed using a white hologram reflecting and scattering plate based on the invention.

2025 RELEASE UNDER E.O. 14176

Figure 40 is illustrative of a part of the process of recording the multicolor hologram display unit shown in Figs. 36 and 37.

Figure 41 is illustrative of another part of the process of recording the multicolor hologram display unit shown in Figs. 36 and 37.

Figure 42 is illustrative of yet another part of the process of recording the multicolor hologram display unit shown in Figs. 36 and 37.

Figure 43 is a sectional schematic of a liquid crystal display device using a conventional hologram color filter.

Figure 44 illustrates one method of fabricating a conventional hologram color display medium.

Figure 45 illustrates another method of fabricating a conventional hologram color display medium.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Reference will now be made to the fundamental principles of the reflection type diffuse hologram of the present invention as well as some embodiments thereof.

Figure 1 illustrates a typical arrangement of how to record a reflection type diffuse hologram according to the present invention. As shown, a diffusing plate 2 having a diffusion angle θ (a maximum diffusion angle) is located into close contact with a hologram photosensitive material 1 such as a photopolymer which can record a volume hologram therein. Parallel light 3 is obliquely incident on the photosensitive material 1 at an angle of incidence α , while parallel light 4

is perpendicularly incident on the diffusing plate 2. Thereupon, the parallel light 4 passes through the diffusing plate 2 to become diffused light 5 having a diffusion angle θ , which, in the photosensitive material 1, in turn interferes with the oblique parallel light 3 incident thereon from the opposite direction to produce interference fringes. In this way, a reflection (or Lippmann) type hologram is formed.

As depicted in Figure 2, parallel illumination light 11 is incident on a reflection type hologram 10 formed as depicted in Figure 1 at the same angle of incidence α at which the parallel light 3 has been incident obliquely on the material 1 to record the hologram 10, whereupon diffused light 12 whose diffusion angle θ is the same as that of the diffused light 5 used to record the hologram 10 is reflected, and diffracted from the reflection type hologram 10.

Consider now the case where such a reflection type hologram 10 is mounted on a rear portion of a car 13 as sketched in Figure 3 as an example. Light from a light source 14 is converted through an optical system 15 (e.g., a paraboloidal mirror) into parallel light 16 to illuminate the reflection type hologram 10 obliquely from above. Then, the light 16 is reflected, and diffracted in the rearward direction of car 13 while the diffusion angle is limited to a desired angle of $\pm\theta$, thereby showing that the preceding car is about to apply a brake or change direction. In addition, the use of such a reflection type diffuse hologram makes it possible to limit the diffusion angle within the preselected range, as mentioned above, so that the diffusion of light at

an angle larger than required can be avoided to prevent wasteful consumption of light from the lamp. Thus, distinct, and bright indication is available.

Alternatively, such a reflection type hologram 10 as mentioned above may be located on a backlight side of a liquid crystal display device 17 as depicted in Figure 4, for instance. Light from a light source 14 is converted through an optical system 15 (e.g., a paraboloidal mirror) into parallel light 16 to illuminate the reflection type hologram 10 obliquely from above. Thereupon, the light 16 is diffracted, and reflected onto the liquid crystal display device 17 while the diffusion angle is limited to the desired angle of $\pm\theta$, so that the light 16 can arrive at the viewer through a transparent portion of the liquid crystal display device 17. In this case, too, the viewing angle of the liquid crystal display device spreads out to the angle $\pm\theta$, but the backlight is confined within the desired angle range, so that wasteful consumption of illumination light can be avoided.

In the case of Figure 1, the reflection type diffuse hologram of the present invention is recorded using the diffusing plate 2 having a limited diffusion angle. Instead, an array of microlenses or a lenticular screen 22, as depicted in Figure 5, may be used as a diffuse optical element. It is noted that the array of microlenses is an arrangement wherein axially symmetric microlenses are two-dimensionally located, and the lenticular screen is an arrangement wherein cylindrical microlenses are one-

dimensionally located, each as shown in section in Figure 5. In this case, there is obtained a reflection type diffuse hologram with a diffusion angle θ corresponding to the collection or divergence angle of the microlenses or cylindrical microlenses forming the array or lenticular screen 22.

An account will then be given of specific embodiments of fabricating such reflection type diffuse holograms as mentioned above. As sketched in Figure 6, a glass substrate 20 was coated thereon with a photosensitive material 1, for instance, Omnidex 706 (a photosensitive film made by Du Pont, U.S.A.), and a PET film 21 in the form of a cover film was applied on the material 1. Then, a diffusing plate 2 formed of a non-glare film having a haze of 25.7% was brought into close contact with the PET film 21 with an index-matching liquid 23 composed of xylene located between them. After this, the diffusing plate 2 was irradiated in the normal direction with object light 4 defined by a parallel beam of Kr laser light (of 647 nm wavelength) and, at the same time, the glass substrate 20 was irradiated at an angle of incidence of 60° with respect to the normal direction with reference light 3 defined by a parallel beam of the same Kr laser light. The ratio between the reference light and the object light was 1:1, and the combined exposure of the two light beams 3 and 4 was 200 mJ/cm^2 . Upon removed from the diffusing plate 2, the photosensitive material 1 was irradiated with 100 mJ/cm^2 of ultraviolet rays, and then heated at 120°C for 2 hours to obtain a reflection type

diffuse hologram having a diffraction efficiency of 65% and a diffraction peak wavelength of 647 nm, and reflecting and diffracting parallel light at a diffusion angle of 12° , said parallel light incident at an angle of incidence of 60° .

5 Notice that diffraction efficiency was determined by measuring transmittance with an automatic recording spectrophotometer (UV-3100PC made by Shimadzu Corporation), and subtracting that transmittance from 100%, and haze was expressed by a value found with NDH-1001DP made by Nippon
10 Denshoku Co., Ltd.

In the same manner as mentioned above, reflection type diffuse holograms were fabricated using diffusing plates 2 with varying hazes. As a result, such diffusion angle characteristics as plotted in Figure 7 were obtained. In
15 Figure 7, black dots represent the diffusion angle characteristics of the diffuse plates 2 themselves, white dots the diffusion angle characteristics of the fabricated reflection type diffuse holograms as found in a direction perpendicular to the drawing sheet of Fig. 2, and white
20 square dots the diffusion angle characteristics of them as found in a plane of the drawing sheet of Fig. 2. From this graph, it is understood that to obtain the diffusion angles of 10° to 35° needed for diffusing plates used for backlighting liquid crystal display devices, and used on
25 automotive brake lamps or direction indicator lamps, it is desired that the haze of the diffusing plate 2 used be 20 to 60%.

It is here noted that the reflection type diffuse hologram according to the present invention is a Lippmann type hologram. Therefore, it is also possible to achieve a reflection type hologram 10 capable of reconstructing not only diffused light 12 but also an image such as a 3M image by using the same reference light 3 as used to record scattered light 5 from the diffusing plate 2 or the micro-lens array or lenticular screen 22 and, before or after recording it, allowing object light to strike from behind the photosensitive material 1, said object light forming an image such a character or picture image in front of the photosensitive material 1 (on the side on which the reference light 3 is incident), thereby multi-recording them in the photosensitive material 1.

While the reflection type diffuse hologram of the present invention, and its fabrication method have been described with reference to its principles and some specific embodiments, it is understood that the present invention is not limited thereto, and so various modifications may be possible.

As can be seen from the foregoing explanations, the aforesaid reflection type diffuse hologram of the present invention is fabricated by the incidence of diffuse light diffusing within the desired angle range and parallel light on both sides of a volume hologram-recording photosensitive material wherein they interfere. It is thus possible to prevent light from a light source from diffusing at an angle larger than required, avoiding wasteful consumption of the

light from the light source, and making bright displays and indications possible. Since the diffusing plate is a volume hologram, it is further possible to achieve easy fabrication of diffusing plates having given characteristics by

5 replication.

Reference will then be made to a specific example of a reflection type of direct-view color display device making use of the hologram color filter according to the present invention.

10 Figure 8 is a sectional schematic of one embodiment of a reflection type of direct-view color display device constructed using a hologram color filter, for instance, one shown in Figure 43. As illustrated, a hologram color filter 55 is spaced away from a side of a transmission type spatial
15 light modulator 36 on which ambient illumination light 33 is to strike, said modulator comprising a liquid crystal display element, a polymer-dispersed type liquid crystal (PDLC) display element, etc., which is regularly divided into pixels 36'. On the back side of the transmission type spatial light
20 modulator 36 there is located a reflection type hologram 30 which will be described at great length, with a light-absorbing layer 35 mounted on the back side of the hologram 30. A black matrix 54 is interposed between adjoining pixels 36' in the transmission type spatial light modulator 36. It
25 is here noted that the distance between the hologram color filter 55 and the reflection type hologram 30 is selected such that it is substantially equal to the light-collecting (focal) distance of each micro-hologram 55'.

094659760

In this case, too, the hologram color filter 55 comprises micro-holograms 55' which are arranged in an array form at the same pitch as that of R, G, and B spectral pixels, corresponding to the period of repetition of R, G, and B spectral pixels in the transmission type spatial light modulator 36, i.e., sets of three adjoining pixels 36' in the transmission type spatial light modulator 36, as viewed in a plane of the drawing sheet. One micro-hologram 55' is located in line with each set of three adjoining pixels 36' in the transmission type spatial light modulator 36, as viewed in the plane of the drawing sheet. The micro-holograms 55' are then arranged in a Fresnel zone plate form such that a green component ray 31G of illumination light 33 incident on the hologram color filter 55 at an angle θ with respect to its normal line is collected in the vicinity of a middle G pixel of the three R, G, and B pixels corresponding to each micro-hologram 55'. Each of the micro-hologram 55' in this case is constructed from a relief, phase, amplitude or other transmission type of hologram which has little, if any, dependence of diffraction efficient on wavelength. The wording "little, if any, dependence of diffraction efficiency on wavelength" used herein is understood to refer specifically to a hologram of the type which diffracts all wavelengths by one diffraction grating, much unlike a Lippmann type hologram which diffracts a particular wavelength alone but does not substantially permit other wavelengths to be transmitted therethrough. The diffraction grating having little dependence of diffraction efficiency on

wavelength diffracts different wavelengths at different angles of diffraction.

In such an arrangement, consider now the case where the ambient light 33 strikes at an angle of incidence θ on the surface side of the hologram color filter 55. The light 33 is subject to wavelength dispersion by the hologram color filter 55, so that the light collection positions for wavelengths are dispersed in a direction parallel with the plane of the hologram color filter 55. If, in this case, the hologram color filter 55 is constructed and arranged such that red, green, and blue wavelength components 31R, 31G, and 31B are diffractively collected in the vicinity of the surface of the reflection type hologram 30 at positions of the pixels R, G, and B displaying red, green, and blue, respectively, the color components pass through the associated pixels 36' without undergoing substantial attenuation by the black matrices 54, and then arrive at the reflection type hologram 30 at the associated positions.

Here, the reflection type hologram 30 is a volume phase (Lippmann) type hologram, and interference fringes 30R, 30G, and 30B in the reflection type hologram 30 - which lie in the vicinity of positions where red, green, and blue diffracted components 31R, 31G, and 31B corresponding to the ambient light 33 having an angle of incidence θ are collected - are formed to separately reflect light of red wavelength, light of green wavelength, and light of blue wavelength, respectively. In addition, the interference fringes 30R, 30G, and 30B are inclined such that the aforesaid red, green

Incidentally, some ambient light 33 incident on the hologram color filter 55 within an angle range of $\theta \pm \Delta$ in the vicinity of the angle of incidence θ , too, is subject to wavelength dispersion by the hologram color filter 55, and hence to color separation as is the case with the color components 31R, 31G, and 31B. However, this light is diffracted at an angle different from that indicated by solid lines in Figure 8. In Figure 8 only principal rays of the green component are indicated by broken lines. For each color component, however, such principal rays are distributed in the vicinity of both sides of the direction of dispersion of diffracted component 31R, 31G or 31B, when the angle of incidence is θ . Accordingly, such diffracted components, too, should be reflected, and diffracted in the same direction as in the case of the reflected light 32R, 32G, and 32B. To achieve this, the interference fringes 30R, 30G, and 30B in the reflection type hologram, too, are continuously formed and distributed at positions corresponding to the pixels R, G, and B.

Thus, all the ambient light 33 striking on the hologram
25 color filter 55 not only at the angle of incidence θ but also
within the angle range of $\theta \pm \Delta$ are subject to wavelength
dispersion thereby. Of the ambient light 33, the red
wavelength component 31R strikes on the red-displaying pixel

R where it is subject to intensity modulation depending on the state of that pixel, and then passes therethrough. This transmitted component is reflected by the interference fringe 30R in the reflection type hologram 30 into reflected light 32R in a certain direction, which in turn passes back through the pixel R from its rear side, and then strikes on, and passes through, the hologram color filter 55 without being now hardly diffracted, finally striking on the eye of the viewer positioned in that direction. The same is also true of the green, and blue wavelength components 31G, and 31B subject to spectral diffraction by the hologram color filter 55. Specifically, they strike on the green, and blue-displaying pixels G, and B where they are subject to intensity modulation depending on the states of those pixels, and then pass therethrough. The transmitted components are reflected by the interference fringes 30G, and 30B into reflected light 32G, and 32B in a certain direction, which in turn pass back through the pixels G, and B from their rear sides, and then strike on, and pass, through the hologram color filter 55 without being now hardly diffracted, finally striking on the eye of viewer positioned in that direction. It is thus possible to display color images by the combination of modulated states of the pixels R, G, and B. It is here noted that one part of ambient light 33 departing from the angle range of $\theta \pm \Delta$, too, is diffracted by the hologram color filter 55, but another part passes therethrough, reaching the reflection type hologram 30. However, since the direction of incidence and wavelength of

the latter part do not comply with the diffraction conditions for the interference fringes 30R, 30G, and 30B, it passes through the reflection type hologram 30 to the light-absorbing layer 35 where it is absorbed; that is, it cannot
5 be reflected onto the viewer.

By using the hologram color filter 55 and reflection type hologram 30 in combination with the transmission type spatial light modulator 36 comprising a collection of pixels, for instance, a liquid crystal display device, it is thus
10 possible to achieve a reflection type of direct-view color display device such as a color liquid crystal display device, which can use ambient light to present bright displays without using any backlight source.

While the reflection type of direct-view display device
15 making use of the hologram color filter of the present invention has been described with reference to the specific embodiment, it is understood that the present invention is not limited thereto, and so various modifications may be possible.

As can be seen from the foregoing explanations, the
20 hologram color filter of the present invention can be used with a reflection type hologram and in combination with a transmission type spatial light modulator comprising a collection of pixels such as a liquid crystal display device,
25 thereby achieving a reflection type of direct-view color display device such as a color liquid crystal display device, which can use ambient light to present bright displays without using any backlight source.

Another embodiment of the reflection type color liquid crystal display device according to the present invention will now be explained.

Prior to making an explanation of that embodiment, a
5 brief account will be given of a volume type reflection
hologram used on a hologram reflection layer. Figure 10 is a
perspective view for illustrating how to record a volume type
reflection hologram, and the action thereof. In Figure
10(a), consider now that coherent parallel object light 71,
10 and reference light 72, each of wavelength λ_B , strike at
angles of incidence of θ_1 , and θ_2 on both sides of a photo-
polymer or other hologram photosensitive material 80 that is
thick with respect to the spatial frequency. (It is noted
that the index λ represents the wavelength of a blue zone, and
15 that indices λ_G , and λ_R will hereinafter stand for the
wavelengths of green, and red zones). They interfere to
record parallel uniform interference fringes in the
photosensitive material 80. As depicted in Figure 10(b),
only illumination light having the same angle of incidence θ_1
20 as that of the object light 71 used for recording or only
components of ambient light 73 with a wavelength lying at and
in the vicinity of λ_B are selectively reflected, and
diffracted by the thus recorded hologram 80', and the thus
reflected, and diffracted light 74 propagates at an exit angle
25 θ_2 and substantially in the same direction as the propagation
direction of the reference light 72 used for recording.
However, light components 75 having other wavelengths λ_G and
 λ_R , and light components striking at angles of incidence other

than θ_1 are allowed to pass through the hologram 80'. The same is also true of holograms recorded using other wavelengths λ_G , and λ_R .

Thus, the volume type reflection hologram is excellent in the ability to select wavelength, and angle, and so can control the half bandwidth of a diffraction wavelength region, the range of diffraction direction, etc. to some extent by selection of photosensitive material thickness, recording conditions, post-treatment conditions, etc.

Here consider now a composite reflection hologram 81 fabricated by periodically arranging sets of three micro-holograms with diffraction wavelengths lying in the blue, green, and red regions in an array form. As depicted in Figure 11, illumination light or ambient light 82 is reflected, and diffracted by the composite reflection hologram 81 upon striking thereon from a given direction, and the thus reflected, and diffracted light 83 propagates in a given direction. However, a blue-reflecting and -diffracting hologram element 81B in the composite reflection hologram 81 diffracts only wavelength λ_B lying in the blue region in a direction thereof. Likewise, a green-reflecting and -diffracting hologram element 81G in the composite reflection hologram 81 diffracts only wavelength λ_G lying in the green region in a direction thereof, while a red-reflecting and -diffracting hologram element 81R diffracts only wavelength λ_R lying in the red region in a direction thereof. It follows that the composite reflection hologram 81 can act as a reflection type hologram color filter comprising reflection

filter elements 81R, 81G, and 81B of the three primary colors R, G, and B.

Figure 9 is an exploded, perspective schematic of one embodiment of the reflection type color display device fabricated using such a reflection type hologram color filter 81 according to the present invention. As illustrated, such a reflection type hologram color filter 81 as mentioned above is located on the back side of a transmission type spatial light modulator 85 built up of a liquid crystal display element, a polymer-dispersed type liquid crystal (PDLC) display element, etc., which is regularly divided into pixels 85', and an absorption layer 87 is positioned on the back side of the reflection type color filter 81. These transmission type spatial light modulator 85, reflection type hologram color filter 81, and absorption layer 87 may be assembled with or without some gaps between them. A black matrix 86 is interposed between adjoining pixels 85' in the transmission type spatial light modulator 85. Three adjoining pixels 85' in the transmission type spatial light modulator 85 constitute together one color display unit 88, in which pixels B, G, and R are blue, green, and red displaying pixels, respectively. Then, the elements forming the reflection type hologram color filter 81 are arranged such that these blue, green, and red displaying pixels B, G, and R in the transmission type spatial light modulator 85 correspond to the blue, green, and red reflecting filter elements 81B, 81G, and 81R in the reflection type hologram color filter 81.

Upon illumination light or ambient light striking on the surface side of the transmission type spatial light modulator 85 in the reflection type color display device assembled as mentioned above, a component 82 of the ambient light that strikes thereon at a given angle of incidence passes through the pixels B, G, and R in the transmission type spatial light modulation 85 while it is subject to intensity modulation depending on their states. At this time, wavelength components λ_B , λ_G , and λ_R in the ambient light 82 are subject to intensity modulation at the same proportion for each pixel B, G, and R. Reference is here made to the light 82 that has passed through the pixels B, G, and R while it has been subject to intensity modulation. The light 82 which has passed through the blue-displaying pixel B strikes on the blue-reflecting filter element 81B where only a blue wavelength component λ_B thereof is selectively reflected, and diffracted in a given direction. Then, the thus reflected, and diffracted light passes back through the blue-displaying pixel B while it is again subject to the same modulation, so that the pixel B emits blue light 89B. However, wavelength components that are not diffracted by the filter element 81B, i.e., λ_G , and λ_R pass through the filter element 81B, and are absorbed by the absorption layer 87 mounted on the back side of the reflection type hologram color filter 81. Likewise, the light 82, which has passed through the green-displaying pixel G while it has been subject to intensity modulation thereby, strikes on the green-reflecting filter element 81G where only a green wavelength component λ_G is selectively

reflected, and diffracted in a given direction. Then, the
thus reflected, and diffracted light passes back through the
green-displaying pixel G while it is again subject to the
same modulation, so that the pixel G emits green light 89G
5 substantially in the same direction as that of the blue light
89B the pixel B emits. Again likewise, the light 82, which
has passed through the red-displaying pixel R while it has
been subject to intensity modulation thereby, strikes on the
red-reflecting filter element 81R where only a red wavelength
10 component λ_R is selectively reflected, and diffracted in a
given direction. Then, the thus reflected, and diffracted
light passes back through the red-displaying pixel R while it
is again subject to the same modulation, so that the pixel R
emits red light 89R substantially in the same direction as
15 those of the green, and blue light 89B, and 89G the pixels B,
and G emit.

Depending on the combination of intensity modulation by
the pixels R, G, and B in the color display unit 88, it is
thus possible to display any desired color with any desired
20 luminance by the additive color mixing of the three displayed
light 89B, 89G, and 89R. It is therefore possible to display
a color image observable from the direction of the displayed
light 89B, 89G, and 89R depending on the combination of the
two-dimensionally located color display units 88 upon
25 displayed.

Figure 12 is a sectional schematic of one modified
embodiment of the display device shown in Figure 9, which
enables images to be displayed even by use of illumination by

backlight. The embodiment of Figure 12 is similar to that of Figure 9 with the exception that an absorption filter 90 instead of the absorption layer 87 is located on the back side of the reflection type hologram color filter 81, and a backlight source 91 is positioned on the back side of the filter 90. This absorption filter 90 is an array comprising an absorption filter element 90G capable of transmitting only light lying in the green region or only light lying in the green, and blue regions at a position of a blue-reflecting filter element 81B in the reflection type hologram color filter 81, an absorption filter element 90R capable of transmitting only light lying in the red region or only light in the red, and green regions at a position of a green-reflecting filter element 81G, and an absorption filter element 90B capable of transmitting only light lying in the blue region or only light lying in the blue, and red regions at a position of a red-reflecting filter element 81R. Correspondingly, a display device-driving circuit is provided such that color information displayed on pixels 85' in the transmission type spatial light modulator 85 changes automatically, for instance, such that information B seen as blue when illuminated by the ambient light 82 changes automatically over to green information G when the backlight source 91 is put on, information G seen as green when illuminated by the ambient light 82 changes automatically over to red information R when the backlight source 91 is put on, and information R seen as red when illuminated by the

ambient light 82 changes automatically over to blue
information B when the backlight source 91 is put on.

When the backlight source 91 is held off, therefore, it
is possible to display a color image by use of illumination
5 by the ambient light 82, as explained with reference to
Figure 9. Upon the backlight source 91 put on, the pixels B,
G, and R change over to G, R, and B, so that color
information displayed on each pixel changes. At a position
where the pixel B is displayed in the case of the reflection
10 type, white light from the backlight source 91 is reduced
through the absorption filter element 90G to only light lying
in the green region or only light lying in the green, and
blue regions. Then, the light lying in the blue region is
cut by the blue-reflecting filter element 81B, so that only
15 the light lying in the green region passes through the
absorption filter 90, and the reflection type hologram color
filter 81. At this time, the green pixel emits green light
92G because the pixel B has changed over to the pixel G.
Likewise, at a position where the pixel G is displayed in the
20 case of the reflection type, white light from the backlight
source 91 is reduced through the absorption filter element
90R to only light lying in the red region or only light lying
in the red, and green regions. Then, the light lying in the
green region is cut by the green-reflecting filter element
25 81G, so that only the light lying in the red region passes
through the absorption filter 90, and the reflection type
hologram color filter 81. At this time, the red pixel emits
red light 92R because the pixel G has changed over to the

pixel R. Moreover, at a position where the pixel R is displayed in the case of the reflection type, the blue pixel emits blue light 92B. Depending on the combination of intensity modulation by the pixels R, G, and B in the color display unit 88 after the backlight source 91 is put on, it is thus possible to display any desired color with any desired luminance by the additive color mixing of the three displayed light 92B, 92G, and 92R. It is therefore possible to display a color image depending on the combination of the two-dimensionally located color display units 88 upon displayed.

According to this embodiment, it is thus possible, and hence favorable, to display color images by use of illumination by ambient light in a bright environment, and by use of illumination by backlight in a dark environment. It is noted that the present invention is not limited to the combination, as shown in Figure 12, of the color elements of the reflection type hologram color filter 81 with the color elements of the absorption filter 90, and so other combinations may be possible.

In this connection, it is noted that the reflection type diffraction hologram elements 81B, 81G, and 81R in the reflection type hologram color filter 81 are two-dimensionally arranged in alignment with the pixels B, G, and R in the transmission type spatial light modulator 85 used with reflected illumination light in three basic matrix patterns as shown in Figure 13. The first is a matrix pattern called a striped type, as shown in Figure 13(a),

wherein hologram elements B, G, and R (indicated by 81B, 81G, and 81R, respectively) appear repeatedly in each row. Notice that dotted lines given in Fig. 13(a) are not needed in actual applications. The second is a matrix pattern called a
5 mosaic type, as shown in Figure 13(b), wherein the period of repetition of a set of hologram elements B, G, and R in one row is shifted by a lead or lag of $1/3$ from that of a set of hologram elements B, G, and R in a row located just above. The third is a matrix pattern called a triangle or delta
10 type, as shown in Figure 13(c), wherein the period of repetition of a set of hologram elements B, G, and R in one row is delayed by $1/2$ from that of a set of hologram elements B, G, and R in a row located just above it. For color filter fabrication, the striped type matrix pattern is preferred
15 because only the one-dimensionally arranged three types of striped_holograms need be provided.

A reflection type hologram color filter 81 comprising a two-dimensional arrangement of such reflection type hologram elements 81B, 81G, and 81R as mentioned above may be obtained
20 by dividing one hologram photosensitive material to zones, and recording interference fringes at recording wavelengths λ_B , λ_G , and λ_R that vary for each zone by such a method as depicted in Figure 10(a). However, it is preferable to use the method already proposed by the present applicant in
25 Japanese Patent Application No. 120016/1993, wherein uniform interference fringes are recorded all over the surface of a hologram photosensitive material such as a photopolymer, as shown in Figure 10(a) for instance, and a swelling film

obtained by mixing a monomer or oligomer, a photo-
polymerization initiator, etc. with a binder polymer is then
brought into close contact with the hologram photosensitive
material with the uniform interference fringes recorded
5 therein, so that the amount of the monomer or oligomer
diffusing from the swelling film into the photosensitive
material with the interference fringes recorded therein is
controlled to regulate fringe spacings to a given amount. It
is also preferable to use the method proposed by the present
10 applicant in Japanese Patent Application No. 192020/1996.

As explained above, it is possible to obtain a
reflection type color display device such as a color liquid
crystal display device which can use ambient light to present
bright displays without recourse to any backlight source by
15 using the reflection type hologram color filter 81 in
combination with the transmission type spatial light
modulator 85 comprising a collection of pixels, such as a
liquid crystal display device or polymer-dispersed type
liquid crystal display device.

20 While the reflection type color display device of the
present invention has been described specifically with
reference to some embodiments, it is understood that the
present invention is not limited to these embodiments, and so
various modifications may be feasible. For instance, a
25 conventional absorption type of RGB color filter may be
additionally used on either side of the transmission type
spatial light modulator 85.

According to the present invention as can be seen from the foregoing explanations, it is possible to obtain a reflection type color display device such as a color liquid crystal display device which can use ambient light to present
5 bright displays without recourse to any backlight source by using the reflection type hologram color filter of the present invention in combination with a transmission type spatial light modulator built up of a collection of pixels and having controllable transmittance for each pixel, the
10 former being located on the back side of the latter.

The hologram-recorded medium of the present invention which is applicable to the reflection type hologram 30 depicted in Figure 8, and the reflection type hologram color filter 81 depicted in Figure 9, and the principles and
15 embodiments of fabricating the same will then be explained with reference to the drawings.

Figure 14 illustrates an exemplified structure of the hologram-recorded medium of the present invention. Specifically, Figure 14(a) is a general plan view of the
20 hologram-recorded medium shown at 101, Figure 14(b) is an enlarged view of an encircled small area in the hologram-recorded medium 101 shown in Figure 14(a), and Figure 14(c) is a sectional view taken along the line C-C' in Figure 14(b).

25 The hologram-recorded medium 101 comprises a volume (Lippmann) type hologram photosensitive material such as a photopolymer, and has a desired color pattern formed thereon, as shown in Figure 14(a). This color pattern is a full-color

pattern, and develops colors for the reasons mentioned later. Alternatively, a plurality of color patterns may have been formed on the photosensitive material so that they can be seen in varying patterns depending on a viewing direction.

- 5 As shown in Figure 14(b), the hologram-recorded medium 101 has its recorded area divided regularly into a micro-dot form of pixels 102. In the embodiment illustrated, the pixels are arranged in a gridiron pattern, but may not necessarily be limited to this pattern. For instance, the pixels may be in
10 a piled pattern. One pixel 102 may be not only quadrangular but also circular, triangular or hexagonal in shape.

- In each pixel 102 there is recorded a volume type of interference fringe 103, as shown sectionally in Figure 14(c). The interference fringes 103 usually comprise a spatial
15 alternation of plane high, and low refractive index zones, which are arranged parallel at a constant pitch. Such interference fringes will hereinafter be called a Bragg grating 103. In Figure 14(c), four adjoining pixels 102_1 to 102_4 are depicted for the purpose of illustrating
20 schematically some possible configurations that the pixels 102 can have as the Bragg grating 103.

- The pixels 102_1 and 102_2 have each the Bragg grating 103 formed parallel with the recording surface, but they are different from each other in terms of pitch (grating
25 spacing). Consider now that light strikes on the pixels 102_1 , and 102_2 . The incident light is diffracted in a direction in which the angles of incidence, and diffraction are equal to each other with respect to the surface of the Bragg grating

103. Since only a light component of wavelength satisfying the Bragg condition is diffracted, however, the wavelength reflected, and diffracted by the pixel 102₁ is different from that reflected, and diffracted by the pixel 102₂ if the angle of incidence is identical. Therefore, if, with respect to a given angle of incidence, the wavelengths diffracted by the pixel 102₁, the pixel 102₂, and a pixel (not shown) in which the Bragg grating 103 differing in pitch from those of the pixels 102₁, and 102₂ is likewise formed parallel on the recording surfaced are assigned to blue, green, and red regions, respectively, it is then possible to record a color pattern of the three primary colors R, G, and B depending on how the pixels 102 are combined. Notice that how to select color tone, and gradation will be described later.

On the other hand, the pixels 102₃ and 102₄ are identical in terms of grating spacing, but differ in terms of the inclination of grating surface (fringe surface). The angle of inclination, and the direction of grating surface can be freely selected. Incident light is diffracted by the Bragg grating 103 in a direction in which the angle of incidence, and the angle of diffraction are equal to each other with respect to the grating surface. Accordingly, since it is only when the Bragg grating 103 is at an angle satisfying the Bragg condition that only light of wavelength satisfying the Bragg condition can be seen in a constant viewing direction different from the direction of incidence of light, the pixels 102₃, and 102₄ cannot simultaneously be observed in the same color when the direction of illumination is specified.

In the case of monochromatic illumination, the pixels 102₃, and 102₄ can selectively be observed depending on a viewing direction. By the combination of such pixels 102, it is thus possible to record a plurality of patterns which change depending on a viewing direction. It is here noted that since one Bragg grating 103 satisfies the Bragg condition at a different wavelength when the angle of incidence varies, one pixel 102₃ or 102₄ changes color depending on a viewing direction if white light for illumination diffuses in the illumination direction.

By variously selecting the pitch, and inclination of the interference fringes 103 to be recorded in the pixels 102, it is thus possible to freely select diffraction angle, and diffraction wavelength. By selecting the pitch, and inclination of the interference fringes 103 from predetermined combinations depending on the positions of the pixels 102, therefore, it is possible to record color patterns which change depending on a viewing direction. It is here noted that since a plurality of different interference fringes 103 recorded in a single pixel 102 in a superposed manner can be diffracted for reconstruction, a plurality of color patterns can freely be recorded in a superposed manner without any limitation on recording areas.

In order to allow the hologram-recorded medium 101 comprising a group of such pixels 102 to express halftone colors other than R (red), G (green), and B (blue) with any desired gradation, R, G, and B dot areas, and their dot percent may be varied to vary gradation, and color tone, as

in the case of printing. It is here noted that the R, G, and B dots may be obtained by two methods, i.e., by dividing a single pixel into three parts, and by associating a set of adjoining three pixels with dots R, G, and B. Both methods
5 are essentially identical with each other.

Figure 15 illustrates a typical area gradation method wherein color tone is varied by varying dot percent. Figure 15(a) illustrates the case where the dot percent between a red dot 104R having interference fringes 103 recorded therein
10 to express R, a green dot 104G having interference fringes 103 recorded therein to express G, and a blue dot 104B having interference fringes 103 recorded therein to express B is 1:1:1 so that they are seen as white by additive color mixing. If, as depicted in Figure 15(b), the areas of the
15 red, and blue dots 104R, and 104B are reduced with a corresponding increase in the area of the green dot 104G, these dots are then seen as green. As the area of the green dot 104G increases relatively, the green color is more enhanced in gradation. It is thus possible to express any
20 desired color tone with any desired gradation by controlling the dot percent between the red, green, and blue dots 104R, 104G, and 104B.

Figure 16 illustrates another dot area gradation method wherein dot percent is again varied to vary color tone. Of
25 red, green, and blue dots 104R, 104G, and 104B with their dot percent being 1:1:1 as depicted in Figure 16(a), the areas of the red, and blue dots 104R, and 104B are reduced by the interposition of blanks 105, so that the area of the green

dot 104G increases relatively. The larger the area of the green dot 10G, the more enhanced the green color is in gradation. This method is similar to an ordinary color printing method, and makes it possible to express any desired color tone with any desired gradation by controlling the dot percent between the red, green, and blue dots 104R, 104G, and 104B.

Figure 17 illustrates a density, not area, gradation method wherein the diffraction efficiency of interference fringes 103 is regulated to any desired value when recording the interference fringes 103, thereby controlling color tone, and gradation. The dot percent between a red dot 104R having interference fringes 103 recorded therein to express R, a green dot 104G having interference fringes 103 recorded therein to express G, and a blue dot 104B having interference fringes 103 recorded therein to express B remains fixed at 1:1:1, and in the case of Figure 17(a), the diffraction efficiencies of the dots 104R, 104G, and 104B are all set at 100%, so that they are seen as white by additive color mixing. When, as shown in Figure 17(b), the diffraction efficiencies of the red, and blue dots 104R, and 104B are reduced to 20%, and 80%, respectively, a halftone color between green and blue is obtained. It is thus possible to express any desired color tone with any desired gradation by controlling the diffraction efficiencies of the red, green, and blue dots 104R, 104G, and 104B.

The aforesaid area, and density gradation methods may be used in combination. It is here noted that the embodiment

depicted in Figure 17 may be modified such that interference fringes 103 for expressing red, green, and blue are recorded in one pixel in a superposed manner with controlled diffraction efficiencies of the interference fringes 103, so that any desired color tone can be expressed with any desired gradation.

Now reference will be made to how to record the Bragg grating 103 having varying grating surface spacing, and inclination for each pixel 102, i.e., how to fabricate the hologram-recorded medium of the present invention. Broadly speaking, this is achieved by four methods, the first one wherein the medium is fabricated from a computer-generated hologram (CGH) by replication, the second wherein the medium is fabricated by use of a mask pattern, and an inclined plane mirror, the third wherein the medium is fabricated by use of a group of micro-mirrors that vary in reflection direction per position, and the fourth wherein the medium is fabricated by recording the Bragg grating while two coherent light beams are moved relatively with respect to a hologram-recording medium.

Several approaches may be envisaged to the CGH replication method. A CGH of the relief type is in itself fabricated by using a computer to calculate interference fringes (a diffraction grating) which diffract light of given wavelength with respect to a given zone alone in a given direction, and drawing the interference fringes on a glass or other substrate with an electron beam resist coated thereon by use of an electron beam, for instance, followed by

development. Likewise, a plurality of CGHs are fabricated, which have different interference fringes in different patterns. CGHs of the reflection or transmission type, too, may be fabricated.

5 According to the first approach, a volume hologram photosensitive material 107 such as a photopolymer is stacked on a reflection type CGH 106, and reconstructing illumination light 108 of given wavelength is then allowed to strike on the CGH 106 through the hologram photosensitive material 107, as shown in Figure 18(a). Thereupon, first-order diffracted light 109 is diffracted from the CGH 106 in the opposite direction, and then interferes with the incident light 108 to produce interference fringes, which are in turn recorded in the photosensitive material 107. Upon removal of the CGH 106, another CGH having different interference fringes in a different pattern is used to record such different interference fringes in the same volume hologram photosensitive material 107, thereby obtaining a hologram-recorded medium 101 of the present invention which has a plurality of patterns recorded therein, said patterns comprising a group of pixels with the same volume type interference fringes 103 recorded therein, as depicted in Figure 14. In connection with the arrangement shown in Figure 18(a), it is noted that a dichroic filter 110 comprising a multilayer interference film and capable of cutting higher-order diffracted light striking on the CGH 106 at angles different from those of the incident light 108, and first-order diffracted light 109 may be interposed between

the CGH 106 and the hologram photosensitive material 107 to prevent unnecessary interference fringes from being recorded therein.

According to another method, a volume hologram photo-
5 sensitive material 107 such as a photopolymer is stacked on a transmission type CGH 106', and reconstructing illumination light 108 of given wavelength is then allowed to strike on the side of the CGH 106' that is not opposite to the hologram material 107, as depicted in Figure 18(b). Thereupon, first-
10 order diffracted light 109 is diffracted from the CGH 106' in the opposite direction. At the same time, reference light 111 is allowed to strike on the photosensitive material 107, so that the first-order diffracted light 109, and reference light 111 interfere in the hologram photosensitive material
15 107 to record interference fringes therein. Upon removal of the CGH 106', another CGH having different interference fringes in a different pattern is used to record such different interference fringes in the same volume hologram photosensitive material 107, thereby obtaining a hologram-
20 recorded medium 101 of the present invention which has a plurality of patterns recorded therein, said patterns comprising a group of pixels with the same volume type interference fringes 103 recorded therein, as depicted in Figure 14. In this case, too, it is noted that a dichroic
25 filter 110 capable of cutting zero-order light, and higher-order diffracted light striking on the CGH 106' at an angle different from that of the first-order diffracted light 109 may be interposed between the CGH 106' and the hologram

00116589 071603
EST 20 6251160

photosensitive material 107 to prevent unnecessary interference fringes from being recorded therein.

According to yet another approach, a volume hologram photosensitive material 107 such as a photopolymer is stacked
5 on a transmission type CGH 106', and reconstructing illumination light 108 of given wavelength is then allowed to strike on the side of the CGH 106' that is not opposite to the hologram material 107, as depicted in Figure 18(c). Thereupon, first-order diffracted light 109 is diffracted
10 from the CGH 106' in the opposite direction, and zero-order light 112 goes straightforward, so that both light 109 and 112 strike on the hologram photosensitive material 107 from the same direction to record a transmission type of volume interference fringes 103 therein. Upon removal of the CGH
15 106', another CGH having different interference fringes in a different pattern is used to record such different interference fringes in the same volume hologram photosensitive material 107, thereby obtaining a hologram-recorded medium of the present invention which has a
20 plurality of patterns recorded therein, said patterns comprising a group of pixels with the same volume type interference fringes 103 recorded therein. However, since, in this case, the recorded volume hologram is of the transmission type, the recorded patterns cannot be seen from
25 the illumination side. Accordingly, as shown sectionally in Figure 19, a reflecting layer 113 such as an aluminum layer must be provided on the back side of the hologram-recorded medium 101 to let it be of the reflection type.

According to the second method using a mask pattern, and an inclined plane mirror, a plurality of mask plates 114 and 114' are fabricated, which have different patterns of openings to be recorded, as depicted in Figure 20. In association with these mask plates 114 and 114', plane mirrors 115 and 115' having different angles of inclination α_1 and α_2 are provided. Of course, one plane mirror may be used to alter the angle of inclination between α_1 and α_2 . Then, as depicted in Figure 20(a), a volume hologram photosensitive material 107 is interposed between the mask plate 114 and the plane mirror 115 such that they are positioned in proximity to one another. Upon the whole of the hologram photosensitive material 107 illuminated by light through the openings in the mask plate 114, the incident light, and light reflected by the plane mirror 115 and tilting dependent on the angle of inclination α_1 interfere in the material 107 to record interference fringes therein. Upon removal of the mask plate 114, another mask plate 114' having a different opening pattern is located with the hologram photosensitive material 107 and the plane mirror 115' such that they are positioned in proximity to one another, thereby recording a different type of interference fringes in the same volume hologram photosensitive material 107. In this way there is obtained a hologram-recorded medium of the invention which has a plurality of patterns recorded therein, said patterns comprising a group of pixels with the same volume hologram photosensitive material 107. In this connection, it is also effective to use primaries-separating original patterns

obtained in the color separation step for printing as the mask plates 114 and 114'.

With the method shown in Figure 20, however, there is possibility that a portion with no volume type interference fringes 103 recorded therein remains, because the distance between the hologram photosensitive material 107 and the plane mirrors 115, 115' becomes too large due to the inclination of the plane mirrors 115, 115', resulting in no interference of the light passing through the openings in the mask plates 114, 114' with the light reflected by the plane mirrors 115, 115' upon passing through the hologram photosensitive material 107. To avoid this, the method of Figure 20 may be modified as depicted in Figure 21(a). For instance, a plurality of off-axis reflection type holograms 123 are provided, which diffract an almost vertically incident light beam 121 at an angle θ into diffracted light 122 propagating in the reflection direction, and have different angles θ . As depicted in Figure 21(b), a volume hologram photosensitive material 107 is interposed between a mask plate 114 and the off-axis reflection type hologram 123 such that they are positioned in proximity to one another, and the whole of the volume hologram photosensitive material 107 is illuminated by the light 121 through the openings in the mask plate 114 to record one interference fringe therein. Upon removal of the aforesaid off-axis reflection type hologram 123, another off-axis reflection type hologram 123 having another angle θ is used to record another interference fringe in the volume hologram photosensitive material 107.

As in the case of Figure 20, there is thus obtained a hologram-recorded medium of the present invention which has a plurality of patterns recorded therein, said patterns comprising a group of pixels with the same volume type interference fringes 103 recorded therein.

According to the third method using a group of micro-mirrors varying in reflection direction per position, a composite reflector 116 is provided, which comprises a collection of micro-mirrors 116' varying in reflection direction per position, as depicted in Figure 22. A volume hologram photosensitive material 107 is positioned in proximity to the surface of the reflector 116. Then, a light beam 117 is permitted to strike on the hologram photosensitive material 107, whereupon the light beam 117 passes through the hologram photosensitive material 107, and is reflected at micro-mirror surfaces 116'₁, 116'₂, and 116'₃ into reflected light 118₁, 118₂, and 118₃, which propagate in different directions. The reflected light 118₁, 118₂, and 118₃ and the incident light 117₁, 117₂, and 117₃ interfere in the hologram photosensitive material 107 to record interference fringes varying per position therein. If a desired pattern is expressed by a group of the micro-mirror surfaces 116' having the same reflection direction, therefore, it is possible to obtain a hologram-recorded medium of the present invention which has a plurality of patterns recorded therein, said patterns comprising a group of pixels with the same volume type interference fringes 103 recorded therein. It is understood that different composite reflectors 116 may be

used to record interference fringes in one hologram photosensitive material 107 in a superposed manner. In this case, the number of patterns and colors to be recorded increase.

In the method of Figure 22, too, an off-axis reflection type
5 micro-holograms 123 varying in diffraction direction per
position, such as those shown in Figure 21(a) may be used in
place of the micro-mirror surfaces 116' varying in reflection
direction per position.

According to the fourth method of recording interference
fringes while two coherent light beams are moved relatively
with respect to a hologram-recording medium, two coherent
thin light beams 119 and 120 intersect each other at a given
relative angle in a specific pixel position in a volume
hologram photosensitive material 107 positioned at a certain
angle, thereby recording in that pixel position a volume type
interference fringe 103 derived from the conditions for
aligning these parts, as depicted in Figure 23(a). In
another pixel position, another volume type interference
fringe 103 derived from the conditions for setting the angle
of the hologram photosensitive material 107 and/or the
relative angles of the light beams 119 and 120 which are
different from those mentioned above is recorded in the
hologram photosensitive material. This process is
sequentially carried out for all pixel positions where the
interference fringes 103 are recorded until a hologram-
recorded medium of the present invention is finally obtained,
which has a plurality of patterns recorded therein, said

patterns comprising a group of pixels with the same volume type interference fringes 103 recorded therein.

While the hologram-recorded medium of the present invention, and the method of fabricating the same have been described with reference to several embodiments, it is understood that the present invention is not limited thereto, and so various modifications may be feasible. In particular, if interference fringes obtained by the interference of diffused light and parallel light, as typically depicted in Figure 1, are used as the interference fringes 103 to be recorded in the pixels 102₁ to 102₄, it is then possible to obtain color pixels 102₁ to 102₄ of the diffuse reflection type. Such a hologram-recorded medium lends itself well fit to the reflection type hologram 30 depicted in Figure 8, and the reflection type hologram color filter 81 depicted in Figure 9.

According to the present invention as explained above, it is possible to obtain a hologram-recorded medium having high diffraction efficiency and capable of reconstructing a bright pattern, because it is a medium which has an imagewise or other pattern comprising a collection of pixels, and in which any one of a volume type of different diffracting gratings comprising volume holograms is assigned to at least a part of the pixels. It is also possible to record a multiplex pattern with no drop of diffraction efficiency. Further, it is possible to record, and reconstruct, a full-color pattern while color tone, and gradation are placed under control by additive color mixing. Furthermore, it is

possible to record, and reconstruct, different patterns which are sharply changeable depending on a viewing direction, and an illumination direction.

Reference will then be made to the principles, and
5 embodiments of the hologram color display medium of the present invention which is applicable to the reflection type hologram 30 of Figure 8, and the reflection type hologram color filter 81 of Figure 9, as well as of the method of medium fabrication.

10 Referring first to the principles of this hologram color display medium, two swelling films obtained by mixing a monomer or oligomer, a photopolymerization initiator, etc. with a binder polymer are provided, as in the case of a photopolymer. Before or after the close contact of these two
15 swelling films with both sides of a photopolymer or other photosensitive material with interference fringes recorded therein, a given area of each swelling film is irradiated with light in a quantity sufficient to deactivate the swelling agent (monomer or oligomer) contained in that area
20 while the other area of the film is not irradiated with light to keep the swelling agent in an active state. Then, the active swelling agent is diffused from the selected areas of the swelling films into the photosensitive material through both its sides, and fixed in place, thereby arbitrarily
25 forming three or four zones, a first zone where the swelling agent is diffused from both sides of the material, a second zone where the swelling agent is diffused from one side of the material, a third zone where the swelling agent is

diffused from the other side of the material, and a fourth zone where the swelling agent is not diffused from either side of the material at all, so that three or four fringe spacings are available to reconstruct a given three- or four-
5 color pattern.

The hologram color display medium of the present invention, and the method of medium fabrication according to the present invention will now be explained specifically with reference to the drawings.

10 Figure 24 illustrates the principle of a first embodiment of the hologram color display medium of the invention. Figure 24(a) is a plan view of a swelling film 131 to be in close contact with the surface side of the material, and Figure 24(b) is a plan view of a swelling film
15 132 to be in close contact with the back side of the material. Each film may have been obtained by mixing a monomer or oligomer, a photopolymerization initiator, etc. with a binder polymer, as in the case of a photopolymer. An area 131n occupying the right 2/3 of the swelling film 131 to
20 be into close contact with the surface side of the material, and an area 132n occupying the right 1/3 of the swelling film 132 to be into close contact with the back side of the material have been deactivated by exposure to light in a quantity sufficient to make inert substantially all of the
25 penetrating active monomer or oligomer in the swelling films. In other words, the swelling film 131 is active in an area 131a occupying the left 1/3 thereof, while the swelling film 132 is active in an area 132a occupying the left 2/3 thereof.

2025 RELEASE UNDER E.O. 14176

Apart from this, a volume hologram 130 comprising plane interference fringes at a constant pitch is recorded in a photopolymer or other photosensitive material, as in the case of Figure 44(a). Then, the swelling films 131, and 132 with some areas deactivated according to a certain deactivation pattern as depicted in Figures 24(a), and 24(b) are brought into close contact with the surface, and back sides of the material, as depicted sectionally in Figure 24(c). The stack is heated under temperature, and time conditions sufficient to diffuse the penetrating active monomer or oligomer from the swelling films 131, and 132 into the volume hologram 130.

After such heat treatment, the swelling films 131, and 132 are held together with, or removed from, the hologram 130. Thereupon, a volume hologram 140 after subjected to the swelling treatment are divided into three areas depending on the degree of swelling, as depicted in Figure 24(d), i.e., an area A swollen by the swelling agent diffused from both swelling films 131 and 132, an area B swollen by the swelling agent diffused from the swelling film 132, and an area C not subjected to swelling at all. The degree of swelling is area $A > \text{area } B > \text{area } C$. If, for instance, the volume hologram 130 is illuminated by light of blue wavelength, the area C does not substantially swell to diffract, and reproduce the blue light in a given direction. On the other hand, the area B having a medium degree of swelling diffracts, and reproduces green light longer in wavelength than blue light in the same direction. Furthermore, the area A having the largest degree of swelling diffracts, and reproduces red

light longer in wavelength than green light in the same direction. It is thus possible to record any desired two- or three-color pattern by the simultaneous swelling of the swelling films 131 and 132 with some areas deactivated according to a given deactivation pattern, which are brought into close contact with both sides of the volume hologram 130.

Figure 25 illustrates the principle of a second embodiment of the hologram color display medium of the present invention. Figure 25(a) is a plan view of a swelling film 131 which is to be first brought into close contact with the surface side of the material for swelling. An area 131n occupying the right 1/2 of the swelling film 131 has been deactivated by exposure to light, as in the case of Figure 24.

Then, as shown in Figure 25(b), the swelling film 131 with the area 131n deactivated according to a constant deactivation pattern as depicted in Figure 25(a) is brought into close contact with the surface of a volume hologram 130 previously obtained by recording plane interference fringes in a photopolymer or other photosensitive material at a constant pitch. The stack is heated under temperature, and time conditions sufficient to diffuse the penetrating active monomer or oligomer from the swelling film 131 into the volume hologram 130.

Another swelling film 132 such as one shown in Figure 25(c) is provided, which is to be brought into close contact with the back side of the material. An area 132n occupying

the central 1/2 of the film 132 has been deactivated by exposure to light, as in the case of Figure 24, except areas 132a, and 132a occupying the left, and right 1/4 of the film 132.

5 After the surface side of the volume hologram 130 has been heated and swollen as depicted in Figure 25(b), the swelling film 132 with the area 132n deactivated according to a constant deactivation pattern as depicted in Figure 25(c) is brought into close contact with the back side of the
10 volume hologram 130, as depicted in Figure 25(d). The stack is heated under temperature, and time conditions sufficient to diffuse the penetrating active monomer or oligomer from the swelling films 132 into the volume hologram 130.

 After such heat treatment, the swelling films 131, and
15 132 are held together with, or removed from, the hologram 130. Thereupon, a volume hologram 140 after subjected to the swelling treatment are divided into four areas depending on the degree of swelling, as depicted in Figure 25(e), i.e., an area A swollen by the swelling agent diffused from both
20 swelling films 131 and 132, an area B swollen by the swelling agent diffused from the swelling film 131 provided on the surface side of the material, and subject to enhanced swelling by heating for the swelling treatment of the back side of the material, an area D swollen by the swelling agent
25 diffused from the swelling film 132 provided on the back side of the material, and an area C not subjected to swelling at all. The degree of swelling is area A > area B > area D > area C. If, for instance, the volume hologram 130 is

0346289-071693
850720-6829760

illuminated by light of blue wavelength, the area C does not substantially swell to diffract, and reproduce blue light in a given direction. On the other hand, the area D having some degree of swelling diffracts, and reproduces bluish green

5 light longer in wavelength than blue light in the same direction. The area B larger in the degree of swelling than the area D diffracts, and reproduces green light longer in wavelength than bluish green light in the same direction.

Furthermore, the area A having the largest degree of swelling
10 diffracts, and reproduces red light longer in wavelength than green light in the same direction. It is thus possible to record any desired three- or four-color pattern by the successive swelling of the swelling films 131, and 132 with some areas deactivated according to a given deactivation
15 pattern, which are brought into close contact with both sides of the volume hologram 130.

In the aforesaid embodiments, the deactivation of the given areas of the swelling films 131, and 132 is carried out by exposure to ultraviolet or other light of given wavelength
20 before the close contact thereof with the volume hologram 130. However, the swelling films 131, and 132 may be deactivated after such close contact. In connection with the case of Figure 24, however, notice that the deactivation of the swelling film 131 or 132 results in the deactivation of
25 the other film 132 or 131 in the same pattern. To avoid this may be achievable by making the swelling films 131 and 132 different in wavelength selectivity from each other. It is thus preferable that the swelling film 131 is deactivated by

light of wavelength coincident with the sensitivity thereof,
and that the swelling film 132 is deactivated by light of
another wavelength coincident with the sensitivity thereof.

Reference will now be made to an embodiment of recording
5 three or four colors by the treatments illustrated in Figures
24, and 25. Specifically, Omnidex 706 (made by Du Pont) was
used as a photopolymer for recording the volume hologram 130
therein, and CTF 75 (made by Du Pont) was used as the
swelling films 131, and 132. The heat treatments explained
10 with reference to Figures 24(c), 25(b), and 25(d) were
carried out at 120°C for 2 hours. As a result, volume
holograms 140 having such diffraction efficiency profiles as
shown in Figures 26, and 27 are obtained in the embodiments
depicted in Figures 24, and 25, respectively. In Figures 26,
15 and 27 curves A to D correspond to the areas A to D in
Figures 24(d), and 25(e). However, notice that the ordinates
represent zero-order light transmittance having complementary
relation to diffraction efficiency, rather than direct
diffraction efficiency. From these figures, it is found that
20 desired color reproducibility can be available.

Patterns obtained with the aforesaid methods are only
three- or four-color patterns. To obtain halftone colors
other than these colors, it is preferable to resort to the
principle of additive color mixing by dot percents of micro-
25 pixels displaying those two, three, and four colors. That
is, a color image is represented by a collection of color
display micro-units comprising pixels A to C or A to D of
such shape as depicted in Figure 24(d) or 25(e). In this

case, any desired color can be expressed by varying the dot percent of the pixels A, B, C, and D on the assumption that the color display unit has a constant area.

In this case, however, although it is possible to
5 control the color of each color display unit yet it is impossible to control the brightness or luminance thereof. Such control is achievable by two methods. The first method involves recording in the volume hologram 130 interference fringes having uniform fringe spacings such that their
10 diffraction efficiency varies depending on the positions of the aforesaid color display units, not interference fringes having uniform diffraction efficiency (refractive index modulation). Notice that the interference fringes have a constant spacing between adjoining fringes, and are each in a
15 plane form, with the refractive index modulation varying per position. In the second method, the volume hologram 130 used may be of a halftone-including absorption type, or may be provided on its diffraction side with a layer such that the intensity of diffracted light varies depending on the
20 position of the aforesaid color display units. Specifically, the volume hologram 130 is provided on its surface with a layer with a halftone-including white-and-black image such as a white-and-black photograph negative recorded therein, or the medium of volume hologram 130 used is of an absorption
25 type such that the intensity of diffracted light varies depending on position.

While the hologram color display unit of the present invention, and the method of fabricating the same have been

09146589 071699
000120 000000

described with reference to several embodiments and examples,
it is understood that the present invention is not limited
thereto, and so various modifications may be possible. In
the examples of Figures 24 and 25, too, the degree of
5 deactivation of the swelling films 131 and 132, for instance,
may be regulated to different values by controlling the
quantity of irradiating light, thereby regulating the degree
of swelling. In the foregoing embodiments, plane
interference fringes have been recorded in the volume
10 hologram 130 at a constant pitch. In this case, too, color
areas A to D of the diffuse reflection type can be obtained
by recording interference fringes produced by the
interference of diffused light and parallel light, as
typically shown in Figure 1. Such a hologram color display
15 medium is suitable for use on the reflection type hologram 30
depicted in Figure 8, and the reflection type hologram color
filter 81 depicted in Figure 9.

According to the hologram color display medium of the
present invention, and the method of fabricating the same as
20 explained above, a stable pattern of two or more different
colors can be reproduced by swelling from a hologram with
uniform interference fringes recorded therein without
recourse to light quantity control, because the hologram is
swollen from both its sides using two swelling films
25 irradiated with a given or more quantity of light according
to the deactivation pattern. In addition, a two-dimensional
diffraction pattern of two or more colors can be displayed by

the combination of the deactivated pattern of one swelling film with that of another swelling film.

Reference will then be made to embodiments of the multicolor hologram display unit according to the present invention, which is applicable to the reflection type hologram 30 of Figure 8, and the reflection type hologram color filter 81 of Figure 9.

Consider here that a hologram display unit 150 designed to display a flower pattern comprising a red flower leaf area 141, a yellowish green flower leaf area 142, an yellow flower leaf area 143 and an orange flower leaf area 144, and a pattern a comprising a green stem area 145 on a colorless transparent background is fabricated from a red diffraction volume hologram, and a green diffraction volume hologram, as shown in Figure 28.

To this end, two volume hologram-recording photosensitive materials 151 and 152 formed of photopolymers, etc. are provided. A red mask pattern 161 such as one depicted in Figure 29 is superposed on one recording photosensitive material 151, and then irradiated with ultraviolet rays 6 to expose the recording photosensitive material 151 to the rays, as depicted in Figure 31(a). Pattern areas 181, 183 and 184 of the mask pattern 161 corresponding to the red, yellow, and orange flower leaf areas 141, 143, and 144 of the hologram display unit 150 are opaque to the ultraviolet rays 146, and a pattern area 182 of the mask pattern 161 corresponding to the yellowish green flower leaf area 142 of the hologram display unit 150 forms a

50% dot area with dots opaque to the ultraviolet rays 146.

Accordingly, portions of the recording photosensitive material 151 corresponding to the pattern areas 181, 183 and 184 are all insensitive to the ultraviolet rays 146 and

5 remain sensitive to other light, and a portion of the photosensitive material 151 corresponding to the pattern area 182 has a 50% dot area part remaining sensitive to other light, too. Thus, portions of the photosensitive material 151 that do not correspond to the pattern areas 181 to 184, 10 and a portion of the photosensitive material 151 that corresponds to another 50% non-dot area part of the pattern area 182 have been deactivated by exposure to the ultraviolet rays 146.

A green mask pattern 162 such as one depicted in Figure 15 30 is superposed on another recording photosensitive material 152, and then irradiated with ultraviolet rays 146 to expose the material 152 to the rays, as depicted in Figure 31(b).

Patterns areas 192, 193 and 195 of the mask pattern 162 corresponding to the yellowish green, yellow, and green

20 flower leaf areas 142, 143, and 145 of the hologram display unit 150 are opaque to the ultraviolet rays 146, and a pattern area 194 of the mask pattern 162 corresponding to the orange flower leaf area 144 of the hologram display unit 150 forms a 50% dot area with dots opaque to the ultraviolet rays

25 146. Accordingly, portions of the recording photosensitive material 152 corresponding to the pattern areas 192, 193 and 195 are all insensitive to the ultraviolet rays 146 and remain sensitive to other light, and a portion of the

2025 RELEASE UNDER E.O. 14176

photosensitive material 152 corresponding to the pattern area 194 has a 50% dot area part remaining sensitive to other light, too. Thus, portions of the photosensitive material 152 that do not correspond to the pattern areas 192 to 195, and a portion of the photosensitive material 151 that corresponds to another 50% non-dot area part of the pattern area 194 have been deactivated by exposure to the ultraviolet rays 146.

Then, a red diffraction volume hologram that reflects, scatters, and diffracts light of red wavelength (e.g., 647 nm), and a green diffraction volume hologram that reflects, scatters, and diffracts light of green wavelength (e.g., 532 nm) are recorded in active (photosensitive) areas of the recording photosensitive materials 151 and 152 with some areas deactivated through the red, and green mask patterns 161 and 162. To this end, a reflecting and scattering plate 163 is located on the back side of the recording photosensitive material 151 or 152 as mentioned above, with a distance d between them, as can be seen from Figures 32(a) and 32(b). Then, light 24 of red wavelength, and light 26 of green wavelength are allowed to strike at a given angle of incidence on the surface side of the photosensitive material 151 or 152, so that light 165 and 167 reflected, and scattered by the reflecting and scattering plate 163 upon passing through the material 151 or 152, and the incident light 164 and 166 interfere in the photosensitive area to record therein the red diffraction volume hologram that reflects, scatters, and diffracts the light of red

wavelength, and the green diffraction volume hologram that reflects, scatters, and diffracts the light of green wavelength. It is here to be noted that the distance d is determined depending on the desired reflection and scattering characteristics of the volume holograms recorded. Of course the plate 163 may be in close contact with the photosensitive material, that is, the distance d may be nearly equal to zero.

Then, films 151' and 152' with the red, and green diffraction volume holograms recorded in the active areas are aligned, and put one upon another to obtain the hologram display unit 150 such as one depicted in Figure 28. Another volume hologram-recording photosensitive material 168 is superposed on the hologram display unit 150, as depicted in Figure 33. Then, illumination light 169 including light of red wavelength (e.g., 647 nm) and light of green wavelength (e.g., 532 nm) is allowed to strike on the recording photosensitive material 168. Thereupon, the incident light 169, light 170 (of red wavelength) diffracted from the hologram area of the film 151', and light 171 (of green wavelength) diffracted from the hologram area of the film 152' interfere in the recording photosensitive material 168 to multi-record interference fringes therein. In this way, the hologram display unit 150 depicted in Figure 28 is obtained.

In what state the areas 141 to 145 of the hologram display unit 150 are arranged is shown in Figures 34(a) to 34(e). Referring first to an area easy to understand, only a

hologram capable of reflecting, and scattering red is recorded in the area 141, as hatched upward to the right in Figure 34(a). This hologram is seen as red in white illumination light. Recorded in the area 145 is only a
5 hologram capable of reflecting, and scattering green (as hatched upward to the left in Figure 34(e)), which is seen as green in white illumination light. Holograms capable of reflecting and scattering red, and green, respectively, are recorded in the area 143 in a superposed manner, as depicted
10 in Figure 34(c). These holograms diffract both wavelengths (e.g., 647 nm and 532 nm) (see Fig. 35), and are seen as yellow by additive color mixing.

In the area 142, micro-dots 147 exist at a 50 dot percent on a background 148, as depicted in Figure 34(b), and
15 holograms capable of reflecting and scattering red, and green, respectively, are recorded on the dots themselves in a superposed manner, as in the case of the area 143, and are seen as yellow. The background 148, which has only a hologram capable of reflecting, and scattering green recorded
20 therein, is seen as green. Thus, the dots 147 exist on the background 148, and the ratio of the dots 174 seen as yellow and the background 148 seen as green is 50:50, and so the holograms are seen as yellowish green by additive color mixing, as shown in Fig. 35.

25 In the area 144, micro-dots 147 exist at a 50 dot percent on the background 148, as depicted in figure 34(d), and holograms capable of reflecting and scattering red, and green, respectively, are recorded on the dots themselves in a

superposed manner, as in the case of the area 143, and are seen as yellow. The background 148, which has only a hologram capable of reflecting, and scattering red recorded therein, is seen as red. Thus, the dots 147 exists on the
5 background 148, and the ratio of the dots 174 seen as yellow and the background 148 seen as red is 50:50, and so the hologram are seen as orange by additive color mixing, as shown in Figure 35.

While the areas 142 and 144 have been described as
10 having a 50 dot percent, it is understood that the dot percent may have any desired value. It is thus possible to obtain any desired halftone colors between green and yellow, and yellow and red.

While the hologram display unit 150 has been described
15 as being constructed from a multi-recorded or stacked unit of two holograms differing in color, i.e., the red diffraction volume hologram, and the green diffraction volume hologram, it is understood that it may be constructed from a multi-recorded or stacked unit of three holograms differing in
20 color by placing an additional blue diffraction volume hologram thereon. A detailed account of how to fabricate such a unit is omitted because needed for this is only the provision of a mask pattern, a recording photosensitive material, and recording wavelength for the added color.

25 Then, reference is made to another multi-color hologram display unit in which a volume hologram recorded at two wavelengths is combined with color tuning, and how to product such a multi-color hologram display unit.

09113091-071698

As shown in Figure 36, two volume hologram-recording photosensitive materials 261 and 262, each formed of a photopolymer, are first provided. A reflecting and scattering plate 223 is located on the back side of one recording photosensitive material 261 with a given distance d between them, as shown in Fig. 36(a). Light 265 of a blue wavelength λ_B strikes at an angle of incidence θ_1 all over an effective area of the recording photosensitive material 261. This incident light is reflected and scattered at the reflecting and scattering plate 223 upon transmission through the recording photosensitive material 261, and the thus reflected and scattered light 266 and the incident light 265 interfere in the photosensitive area to record therein a blue diffraction volume hologram 261' that reflects, scatters, and diffracts light of blue wavelength uniformly from the entire effective area. Likewise, the reflecting and scattering plate 223 is located on the back side of the recording photosensitive material 262 with a given distance d between them, as illustrated in Fig. 36(b). Light 267 of a green wavelength λ_G strikes at the same angle of incidence θ_1 all over an effective area of the recording photosensitive material 262. This incident light is reflected and scattered at the reflecting and scattering plate 223 upon transmission through the recording photosensitive material 262, and the thus reflected and scattered light 268 and the incident light 267 interfere in the photosensitive area to record therein a green diffraction volume hologram 262' that reflects, scatters, and diffracts light of green wavelength uniformly

2025 RELEASE UNDER E.O. 14176

from the entire effective area. It is here to be understood that the distance d is determined depending on the desired reflection and scattering characteristics of the volume hologram to be recorded. Of course, the plate 223 may be in
5 close contact with the recording material, that is, the distance d may be nearly equal to zero.

As illustrated in Fig. 36(c), the aforesaid blue, and green diffraction volume holograms 261' and 262' are put one upon another to prepare a hologram assembly. Another volume
10 hologram-recording photosensitive material 263 is put on the hologram assembly in close contact or spaced-away relation thereto. Coherent replicating-illumination light 269 including wavelengths λ_B and λ_G strikes at an angle of incidence θ_1 on the recording photosensitive material 263,
15 whereupon the illumination light 269 and reflected, scattered and diffracted light 270 comprising a light component of wavelength λ_B diffracted through the volume hologram 261' and a light component of wavelength λ_G diffracted through the volume hologram 262' interfere in the recording
20 photosensitive material 263 to make a hologram 263' in which there are multi-recorded a blue diffraction volume hologram that reflects, scatters, and diffracts light of blue wavelength uniformly from the entire surface of its effective area, and a green diffraction volume hologram that reflects,
25 scatters, and diffracts light of green wavelength. It is here to be noted that the hologram 263' in which there are multi-recorded a blue diffraction volume hologram that reflects, scatters, and diffracts light of blue wavelength

09-16500-0159

uniformly from the entire surface of its effective area, and a green diffraction volume hologram that reflects, scatters, and diffracts light of green wavelength may also be made by exposing a single recording photosensitive material 263 to
5 light concurrently or successively as shown in Figs. 36(a) and 36(b).

Then, as shown in Fig. 37(a), a swelling film 271 (hereinafter called a color tuning film), which is obtained as explained with reference to Figures 44 and 45, that is, by
10 mixing a monomer or oligomer and a photopolymerization initiator, etc. with a binder polymer as in the case of a photopolymer, is superposed on the thus prepared hologram 363'. While a mask 272 having a repeated pattern comprising transparent openings such as dots is placed over the color
15 tuning film 271, the color tuning film 271 is irradiated with ultraviolet radiation or other light 273 in a quantity sufficient to polymerize and thereby deactivate a nearly all part of the active penetrating monomer or oligomer contained therein, so that portions of the color tuning film 271
20 corresponding to the transparent openings in the mask 272 are substantially deactivated. After such irradiation, the assembly is thermally treated under temperature and time conditions sufficient to diffuse the active penetrating monomer or oligomer from the color tuning film 271 into the
25 hologram 263'. Consequently, in a portion - shown by b in Fig. 37(b) - of the hologram 263' corresponding to a position on which the light 273 does not strike, the distance between the interference fringes of the blue diffraction volume

00146559-1071098

hologram becomes wide, providing a green diffraction volume
hologram that reflects, and diffracts light of green
wavelength. In the same portion b, the distance between the
interference fringes of the green diffraction volume
5 hologram, too, becomes large, providing a red diffraction
volume hologram that reflects, and diffracts light of red
wavelength. In a portion - shown by a in Fig. 37(b) - of the
hologram 263' corresponding to a position on which the color
tuning film 271 is substantially deactivated by the incident
10 light 273, both the blue, and green diffraction volume
holograms remain substantially unchanged.

Then, as shown in Fig. 37(c), the hologram 263' color-
tuned as mentioned above is irradiated at the same angle of
incidence θ_1 as in hologram recording with illumination light
15 274 including green wavelengths λ_G , λ_G' and red wavelength λ_R .
Thereupon, the light 274 is reflected, scattered, and
diffracted from the portion a of the hologram 263' to produce
light having wavelengths λ_B and λ_G while it is reflected,
scattered, and diffracted from the portion b of the hologram
20 263' to produce light 275' having wavelengths λ_G' and λ_R . The
light 275 is seen as cyan blue while the light 275' is seen
as yellow.

Figs. 38(a) and 38(b) are illustrative of curves showing
one example of diffraction efficiency profiles of the volume
25 hologram at the portions a and b of hologram 263'. It is
here to be noted that the ordinates show zero-order light
transmittances complementary to diffraction efficiency,
rather than a direct indication of diffraction efficiency.

In this example, Omnidex 706 (Du Pont) was used as the photopolymer for the recording photosensitive material 263 and CTF 75 (Du Pont) as the color tuning film 271. The thermal treatment for the diffusion of the active penetrating monomer or the like was carried out at 120°C for 2 hours. From Figure 38, it is well found that light having a blue wavelength λ_B and a green wavelength λ_G is reflected, scattered, and diffracted from the portion a which has not been subjected to color tuning (see Fig. 38(a)), and that light having a green wavelength λ_G' and a red wavelength λ_R is reflected, scattered, and diffracted from the portion b which has been subjected to color tuning.

If the portions a and b are fine, the hologram 263' is as a whole seen as an added cyan blue and yellow color by additive color mixing. However, it is possible to reconstruct halftone colors because the mixing ratio of the cyan blue and yellow can be varied depending on area gradation or density gradation by control of the ratio of the area of the transparent portion of mask 272 (corresponding to the area of portions a) and the area of the opaque portion of mask 272 (corresponding to the area of portions b), the transmittance of the transparent portion of mask 272, e.g., dots, the quantity of light 273 used, the intensity ratio of blue and green laser light, and the thermal treatment conditions. If the mask 272 is designed such that the area gradation or density gradation varies in a position-depending manner, it is then possible to construct the hologram 263' in the form of a multi-color hologram display unit.

By similar control, it is also possible to construct the hologram 263' in the form of a hologram reflecting and scattering plate which is as a whole seen as nearly white or greenish white by additive color mixing of cyan blue and yellow. Such a hologram reflecting and scattering plate may be used as a bright reflecting and scattering plate for liquid crystal display devices.

Here, a liquid crystal display apparatus using such a hologram reflecting and scattering plate will be briefly explained. The white hologram reflecting and scattering plate according to the present invention is a hologram designed to diffuse and reflect light incident from a specific direction (the direction of illumination light 274 in Fig. 37(c)) to only a direction defined as a viewing region. As illustrated in section in Figure 39, a liquid crystal display apparatus is built up of a liquid crystal display device 280, and a white hologram reflecting and scattering plate 276 located on the back side thereof. Illumination light 277 incident from the display side of the liquid crystal display device 280 is converted into diffused light 278 which has been diffused and reflected only in an angle range θ commensurate with the viewing region of the liquid crystal display device, so that displays can be achieved in the bright place without recourse to any self-emission type backlight. For instance, the liquid crystal display device 280 comprises a twisted nematic or other liquid crystal layer 285 sandwiched between two glass substrates 281 and 282. One glass substrate 282 is provided

on its inner surface with uniform transparent opposite electrodes 284, and the other glass substrate 281 is provided on its inner surface with transparent display electrodes 283, independent per pixel, and a black matrix (not shown). It is
5 here to be noted that in the case of a color display apparatus, the other glass substrate 281 is additionally provided on its inner surface with transparent display electrodes 283, color filters, and black matrices independent per liquid crystal cells R, G, and B. Sides of the
10 electrodes 283 and 284 opposite to the liquid crystal layer 285 are provided with aligning layers (not shown). The outer surface of the glass substrate 281 on the viewing side is provided with a polarizing plate 286, and the outer surface of the glass substrate 282 on the back side of the glass
15 substrate 281 is provided with a polarizing plate 287, for instance, with the transmission axes thereof being perpendicular with respect to each other. By controlling the voltage applied between the transparent display electrodes and the transparent opposite electrodes to vary the state of
20 transmission, it is possible to selectively display figures, characters, symbols, patterns, etc. on the liquid crystal display apparatus.

In the embodiment of Figure 36, the blue, and green diffraction volume holograms are recorded all over the
25 surfaces of the effective areas of recording photosensitive materials 261, and 262, respectively. Here consider the case where volume holograms are recorded in the desired pattern areas alone at the stages of Figs. 36(a) and 36(b). First,

two volume hologram-recording photosensitive materials 291 and 292 are provided. As in Figure 31, a blue mask pattern is superposed on the recording photosensitive material 291 for recording a blue diffraction volume hologram therein.

5 Then, the recording photosensitive material 291 is irradiated with ultraviolet radiation from the mask pattern, so that a pattern area 294 of the recording photosensitive material 291 is exposed to, and deactivated, by the ultraviolet radiation, as shown in Fig. 40(a). A green mask pattern is, on the
10 other hand, put on the recording photosensitive material 292 for recording a green diffraction volume hologram therein. Then, the recording photosensitive material 292 is irradiated with ultraviolet radiation from the mask pattern, so that a pattern area 295 of the recording photosensitive material 292
15 is exposed to, and deactivated, by the ultraviolet radiation, as shown in Fig. 40(b).

Following this, as shown in Figs. 40(a) and 40(b), blue, and green diffraction volume holograms 291', and 292' are recorded in the remaining active areas of the recording
20 photosensitive materials 291, and 292, respectively, as is the case with Figs. 36(a) and 36(b), said blue diffraction volume hologram 291' being designed to reflect, scatter, and diffract light of blue wavelength from the active area alone, and said green diffraction volume hologram 292' being
25 designed to reflect, scatter, and diffract light of green wavelength from the active area alone. Thereafter, as shown in Fig. 40(c), the blue, and green diffraction volume holograms 291', and 292' are put one upon another, as is the

case with Fig. 36(c), thereby forming a hologram assembly. After another volume hologram-recording photosensitive material 293 is located in close contact with, or spaced slightly away from, the hologram assembly, it is irradiated with coherent replicating illumination light 269 including wavelengths λ_B and λ_G at an angle of incidence θ_1 , so that the incident illumination light 269, and the reflected, scattered, and diffracted light 270 comprising light diffracted through the volume hologram 291' and having wavelength λ_B and light diffracted through the volume hologram 292' and having wavelength λ_G interfere in the photosensitive material 293 to make a hologram 293' in which there are multi-recorded a blue diffraction volume hologram that reflects, scatters, and diffracts light of blue wavelength from a separately patterned area, and a green diffraction volume hologram that reflects, scatters, and diffracts light of green wavelength from a separately patterned area. It is here to be noted that the hologram 293' in which there are multi-recorded a blue diffraction volume hologram that reflects, scatters, and diffracts light of blue wavelength uniformly from the separately patterned area, and a green diffraction volume hologram that reflects, scatters, and diffracts light of green wavelength from the separately patterned area may also be made by exposing a single recording photosensitive material 293 to light concurrently or successively as shown in Figs. 40(a) and 40(b).

In the thus obtained or multi-recorded hologram 293', blue diffraction volume hologram areas B and green

diffraction volume hologram areas G are alternately arranged side-by-side, as illustrated in Figs. 41(a) and 42(a).

Although not illustrated, the blue diffraction volume hologram area B may overlap partly with the green diffraction volume hologram area G. In some cases, there may be a region in which both the blue, and green diffraction volume hologram areas B, and G are not recorded, although not again

illustrated. Referring to Figs. 41(a) and 42(a), the blue, and green diffraction volume hologram areas B, and G are

alternately arranged side-by-side. However, Fig. 41(a) shows an embodiment wherein the area G is twice as wide as the area B, and Fig. 42(a) shows an embodiment wherein the area B is twice as wide as the area G. In the hologram 293' wherein the blue, and green diffraction volume hologram areas G, and B are multi-recorded, the blue and/or green diffraction volume holograms may be color-tuned through a color tuning film 271, as in Figs. 37(a) and 37(b). In this case, the distance between the interference fringes of the blue diffraction volume hologram becomes large, providing a green diffraction volume hologram that reflects, and diffracts light of green wavelength, and so is the distance between the interference fringes of the green diffraction volume hologram, providing a red diffraction volume hologram that reflects, and diffracts light of red wavelength.

Referring to Fig. 41(b), an area c of the color tuning film 271 is deactivated and so unavailable for color tuning. In other words, effective for color tuning is an area d where half of the green diffraction volume hologram area G in the

hologram 293' is converted into a red diffraction volume
hologram area R. Referring to Fig. 42(b), an area e of the
color tuning film 271 is deactivated and so unavailable for
color tuning. In other words, effective for color tuning is
5 an area f where half of the blue diffraction volume hologram
area B in the hologram 293' is converted into a green
diffraction volume hologram area G, which is in turn
converted into a red diffraction volume hologram area R. In
any case, three areas of substantially similar size and
10 located adjacent to one another provide blue, green, and red
diffraction volume hologram areas B, G, and R; each area
provides a fine pixel. By appropriately selecting the area
or density gradation of the pixels, the pattern and
transmittance of the mask for the deactivation of the
15 recording photosensitive materials 261 and 262, and the
pattern and transmittance of the mask for the deactivation of
the color tuning film 271, it is thus possible to display any
desired color pattern, thereby expressing any desired color
at any desired position by additive color mixing of RGB.

20 It is here to be noted that in the hologram 263' or 293'
partially color tuned by the color tuning film 271, the color
tuning film 271 may be either released from or integral with
the final hologram display unit.

While the multicolor hologram display unit of the
25 invention has been described with reference to several
embodiments, it is understood that the invention is not
limited thereto, and so various modifications may be
possible. It is also understood that volume holograms of the

transmission scattering type or the type that enables 3D
images or other pictures to be reproduced may be used as
holograms. Furthermore, it is understood that the dots used
herein may be not only a collection of patterns such as
5 micro-circles or rectangles but also a collection of micro-
stripes.

In the multicolor hologram display unit of the invention
as can be understood from the foregoing explanation, halftone
pattern areas defined by dot percents are formed by
10 superposing hologram dots of one color on a background
hologram of another color. Thus, the accuracy needed for
alignment of hologram plates having different colors may be
much more reduced as compared with the case where dot
alignment is required. Also, since halftone colors are
15 produced by dot percents, not by hologram-recording
intensity, they can be reconstructed in a stable manner and
with good reproducibility. It is thus possible to mass-
produce multicolor hologram display units in a stable manner
and with good reproducibility.

20 According to another multicolor hologram display unit of
the invention, it is possible to reproduce a color different
from recorded one by simple color tuning of a part or local
area of the multi-recorded volume hologram using a color
tuning film. It is thus possible to produce a large amount
25 of any color pattern by additive color mixing of the recorded
color and the color-tuned color with good reproducibility.
It is also possible to easily obtain a hologram reflecting

0344589 071608

and scattering plate that is substantially white all over the surface.

0044509 074690

WHAT WE CLAIM IS:

1. A reflection type diffuse hologram characterized by reflecting, and diffracting light incident thereon at an angle with respect to a normal direction while it is diffused
5 within a desired angle range.

2. The reflection type diffuse hologram of claim 1, characterized in that an angle of diffusion lies within a range of 10° to 35° .

3. A reflection type diffuse hologram, characterized
10 by having been formed by allowing scattered light that diffuses within a desired angle range, and parallel light to strike on both surfaces of a volume hologram-recording photosensitive material, and interfere therein.

4. The reflection type diffuse hologram of any one of
15 claim 1 to 3, characterized in that an image has simultaneously been recorded in a reconstructible fashion.

5. The reflection type diffuse hologram of any one of claim 1 to 3, characterized by being located on a backlight side of a liquid crystal display device for diffuse
20 illumination purposes.

6. A method for fabricating a reflection type diffuse hologram characterized in that a transmission type diffusing plate having a diffusion angle characteristic within a desired angle range is located in close contact with, or in
25 proximity to, a volume hologram-recording photosensitive material, and two light beams are allowed to strike on front and back sides of the combined diffusing plate and photosensitive material for interference recording.

7. The method for fabricating a reflecting type diffuse hologram according to claim 6, characterized in that the transmission type diffusing plate is a diffusing plate of a 20% to 60% haze.

5 8. The method for fabricating a reflecting type diffuse hologram according to claim 6, characterized in that the transmission type diffusing plate is an array of microlenses.

9. The method for fabricating a reflecting type diffuse hologram according to claim 6, characterized in that the transmission type diffusing plate is a lenticular screen.

10 10. A reflection type of direct-view color display device using a hologram color filter, characterized by comprising a hologram color filter composed of an array of element light-collecting holograms,

15 each of said element light-collecting holograms comprising a hologram color filter for subjecting white light incident thereon at a given angle with respect to a normal line of a hologram-recorded surface to wavelength dispersion in a direction substantially along said hologram-recorded surface for spectral diffraction, a reflection type hologram located in the vicinity of a light-collection surface thereof, and a transmission type spatial light modulator located between said hologram color filter and said

20 reflection type hologram.

25 11. The reflection type of direct-view color display device using a hologram color filter according to claim 10, characterized in that said reflection type hologram has

09116589-171698

interference fringes recorded in the vicinity of a position on which said white light strikes while said white light is separated into each spectral component of each color, said interference fringes reflecting light of wavelength of each color in an identical direction.

12. The reflection type of direct-view color display device using a hologram color filter according to claim 11, characterized in that said reflection type hologram has diffusibility.

10 13. The reflection type of direct-view color display device using a hologram color filter according to any one of claims 10 to 12, characterized in that said transmission type spatial light modulator comprises a liquid crystal display element.

15 14. A reflection type color display device, characterized by comprising a transmission type spatial light modulator comprising a collection of pixels, and having a controllable transmittance per pixel, and a reflection type hologram color filter located on a back side of said
20 modulator.

15. The reflection type color display device of claim 14, characterized in that said reflection type hologram color filter comprises periodically arranged volume hologram elements varying in reflection, and diffraction wavelength
25 for each position of pixels in said transmission type spatial light modulator.

16. The reflection type color display device of claim 15, characterized in that said reflection type hologram color filter has diffusibility.

17. The reflection type color display device of any one of claims 14 to 16, characterized in that said reflection type hologram color filter has an absorption layer located on a back surface thereof.

18. The reflection type color display device of any one of claims 14 to 16, characterized in that said reflection type hologram color filter is provided on a back surface thereof with an absorption type color filter, which is provided on a back surface thereof with a backlight source, so that color information is interchangeable when said backlight source is turned on, said color information being displayed on each pixel in said transmission type spatial light modulator.

19. The reflection type color display device of any one of claims 14 to 17, characterized in that said transmission type spatial light modulator comprises a liquid crystal display element.

20. The reflection type color display device of any one of claims 14 to 17, characterized in that said transmission type spatial light modulator comprises a polymer-dispersed type liquid crystal display element.

21. A hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, characterized in that any one of a plurality of volume type diffraction gratings comprising volume holograms

and differing from each other is assigned to at least a part of said pixels.

22. The hologram-recorded medium of claim 21, characterized in that a plurality of volume type diffraction gratings comprising said volume holograms and differing from each other include at least three volume type diffraction gratings which are identical in orientation of grating surface with each other but different in grating spacing from each other.

23. The hologram-recorded medium of claim 21 or 22, characterized in that at least two of a plurality of mutually different volume type diffraction gratings are multi-recorded in at least a part of the pixels.

24. The hologram-recorded medium of any one of claims 21 to 23, characterized in that a volume type diffraction grating that expresses red, a volume type diffraction grating that expresses green, and a volume type diffraction grating that expresses blue are assigned to three dot areas into which at least a part of the pixels is divided, or to three adjoining pixels, so that color tone or gradation is controlled by varying a dot percent occupied by said volume type diffraction gratings, or a diffraction efficiency ratio between said volume type diffraction gratings.

25. The hologram-recorded medium of any one of claims 21 to 24, characterized by having a reflecting layer on a back surface thereof.

26. The hologram-recorded medium of any one of claims 21 to 25, characterized in that each pixel has diffusibility.

094659-0000

27. The hologram-recorded medium of any one of claims 21 to 26, characterized by being used as a reflection type hologram color filter.

28. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising volume holograms and differing from each other is assigned to at least a part of said pixels, characterized by stacking a volume hologram photosensitive material on a reflection type relief hologram, and striking reconstructing illumination light of given wavelength on said reflection type relief hologram through said volume hologram photosensitive material, so that interference fringes produced by interference of light diffracted from said reflection type relief hologram and the incident light are recorded in said volume hologram photosensitive material.

29. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising volume holograms and differing from each other is assigned to at least a part of said pixels, characterized by stacking a volume hologram photosensitive material on a transmission type hologram, and striking reconstructing illumination light of given wavelength on a side of said transmission type hologram that is not opposite to said volume hologram photosensitive material, so that interference fringes

produced by interference of light diffracted from said transmission type hologram and reference light incident on said volume hologram photosensitive material are recorded in said volume hologram photosensitive material.

5 30. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising volume holograms and differing from each other is assigned to
10 at least a part of said pixels, characterized by stacking a volume hologram photosensitive material on a transmission type hologram, and striking reconstructing illumination light of given wavelength on a side of said transmission type hologram that is not opposite to said volume hologram
15 photosensitive material, so that interference fringes produced by interference of light diffracted from said transmission type hologram and zero-order transmitted light are recorded in said volume hologram photosensitive material, followed by provision of a reflecting layer on a back side of
20 said volume hologram photosensitive material.

 31. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising
25 volume holograms and differing from each other is assigned to at least a part of said pixels, characterized by locating a mask plate having an opening pattern on one side of a volume hologram photosensitive material and a reflecting mirror on

another side of said volume hologram photosensitive material,
said reflecting mirror having a specific angle of inclination
with respect to said volume hologram photosensitive material,
and striking a light beam on said volume hologram

5 photosensitive material through said opening pattern in said mask plate, so that interference fringes produced by interference of the incident light and light reflected from said reflecting mirror are recorded in said volume hologram photosensitive material.

10 32. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising volume holograms and differing from each other is assigned to
15 at least a part of said pixels, characterized by locating a mask plate having an opening pattern on one side of a volume hologram photosensitive material and an off-axis reflection type hologram on another side of said volume hologram photosensitive material, said off-axis reflection type
20 hologram diffracting a light beam incident at a given angle of incidence in an opposite direction at a specific angle with respect thereto, and striking a light beam on said volume hologram photosensitive material through said opening pattern in said mask plate, so that interference fringes
25 produced by interference of the incident light and light diffracted from said off-axis reflection type hologram are recorded in said volume hologram photosensitive material.

33. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising
5 volume holograms and differing from each other is assigned to at least a part of said pixels, characterized by locating a composite reflector comprising a collection of micro-mirror surfaces varying in reflection direction per position on a back side of a volume hologram photosensitive material, and
10 striking a light beam on a surface side of said volume hologram photosensitive material, so that interference fringes produced by interference of the incident light and light reflected from said composite reflector are recorded in said volume hologram photosensitive material.

15 34. A method of fabricating a hologram-recorded medium which is an imagewise or other pattern-recorded medium comprising a collection of pixels, and in which any one of a plurality of volume type diffraction gratings comprising volume holograms and differing from each other is assigned to
20 at least a part of said pixels, characterized by striking two coherent thin light beams at a position of each of pixels in a volume hologram photo-sensitive material while said beams intersect at a relative angle corresponding to said position, thereby recording in said volume hologram photosensitive
25 material interference fringes having an inclination and a pitch depending on said pixel position.

35. A hologram color display medium which is a hologram color display medium having interference fringes of light

05416589 074698

5

10

20

25

39. The hologram color display medium of claim 37,
characterized in that said hologram itself or a diffraction-
side surface thereof is designed such that absorptance
changes depending on positions of said color display micro-
5 units.

40. The hologram color display medium of any one of
claims 35 to 39, characterized in that said hologram is a
volume phase type hologram.

41. The hologram color display medium of claim 40,
10 characterized in that said hologram is a hologram recorded in
a photopolymer.

42. The hologram color display device of any one of
claims 35 to 41, characterized by having diffusibility.

43. The hologram color display medium of any one of
15 claims 35 to 42, characterized by being used in the form of a
reflection type hologram color filter.

44. A method for fabricating a hologram color display
medium including a hologram having interference fringes of
light recorded in a thickness direction of a film, wherein
20 two swelling films each containing a penetrating monomer or
oligomer that is diffusible externally from a surface of said
film, said penetrating monomer or oligomer being deactivated
according to a given deactivation pattern, are used so that
said hologram is swollen by said penetrating monomer or
25 oligomer diffused from both surfaces of said hologram at
different degrees of swelling depending on position,
characterized in that

before or after the close contact of the two swelling films, in which the penetrating monomer or oligomer contained in that position is deactivated by irradiation of a given or more quantity of light, with both surfaces of said hologram, 5 said two swelling films are irradiated according to said given deactivation pattern with a given or more quantity of light, and

said hologram with the thus deactivated swelling films brought into close contact with both surfaces thereof is 10 heated, thereby diffusing said penetrating monomer or oligomer from active areas of said swelling films into said hologram.

45. A method for fabricating a hologram color display medium including a hologram having interference fringes of 15 light recorded in a thickness direction of a film, wherein two swelling films each containing a penetrating monomer or oligomer that is diffusible externally from a surface of said film, said penetrating monomer or oligomer being deactivated according to a given deactivation pattern, are used so that 20 said hologram is swollen by said penetrating monomer or oligomer diffused from both surfaces of said hologram at different degrees of swelling depending on position, characterized in that

before or after the close contact of one swelling film, 25 in which the penetrating monomer or oligomer contained in that position is deactivated by irradiation of a given or more quantity of light, with one surface of said hologram, said one swelling film is irradiated according to said given

09430000-07400

deactivation pattern with a given or more quantity of light,

said hologram with the thus deactivated swelling film brought into close contact with said one surface is heated, thereby diffusing said penetrating monomer or oligomer from
5 an active area of said one swelling film into said hologram,

before or after the close contact of another swelling film, in which the penetrating monomer or oligomer contained in that position is deactivated by irradiation of a given or more quantity of light, with another surface of said
10 hologram, said another swelling film is irradiated according to said given deactivation pattern with a given or more quantity of light, and

said hologram with the thus deactivated swelling film brought into close contact with said another surface is again
15 heated, thereby diffusing said penetrating monomer or oligomer from an active area of said another swelling film into said hologram.

46. The method for fabricating a hologram color display medium according to claim 44 or 45, characterized in that
20 said hologram is a volume phase type hologram.

47. The method for fabricating a hologram color display medium according to claim 46, characterized in that said hologram is a hologram recorded in a photopolymer.

48. A multicolor hologram display unit in which volume
25 holograms that diffract light of at least tow different wavelengths are multi-recorded or superposed one upon another, characterized by including a halftone color pattern area comprising a dot area with two holograms of said volume

holograms multi-recorded or superposed one upon another, and a background area for each other of said two holograms recorded between dots.

49. A multicolor hologram display unit in which volume
5 holograms that diffract light of at least two different wavelengths are multi-recorded or superposed one upon another, characterized by including a halftone color pattern area wherein, in a micro-dot portion in an area having one hologram of said volume holograms recorded all over a surface
10 thereof, there is multi-recorded or superposed another hologram.

50. The multicolor hologram display unit of claim 48 or 49, characterized in that in addition to said halftone color pattern area, there are an original color pattern area with
15 the respective holograms independently recorded therein, and another halftone color pattern in which two or more different holograms are multi-recorded or superposed all over a surface thereof.

51. The multicolor hologram display unit of any one of
20 claims 48 to 50, characterized by including an area having a different dot percent.

52. The multicolor hologram display unit of any one of claims 48 to 51, characterized in that said hologram comprises a reflection scattering type hologram.

53. A multicolor hologram display unit comprising
25 volume holograms multi-recorded therein, said volume holograms diffracting light of at least two different wavelengths, characterized by further comprising a color

tuning film containing a penetrating monomer or oligomer that is diffusible from a surface thereof to an outside thereof, said penetrating monomer or oligomer being deactivated according to a given deactivation pattern, so that said
5 monomer or oligomer is diffused from said color tuning film, whereby a portion of said volume holograms in no alignment with said deactivated pattern is swollen to diffract light of a wavelength that is different from a wavelength that is diffracted by a portion of said volume holograms in alignment
10 with said deactivated pattern.

54. The multicolor hologram display unit of claim 53, characterized in that said multi-recorded volume holograms are recorded all over a surface thereof, with said deactivation pattern comprising dots.

15 55. The multicolor volume hologram display unit of claim 54, characterized by being used as a hologram reflecting and scattering plate for liquid crystal display apparatus.

20 56. The multicolor volume hologram display unit of claim 54, characterized by including an area having a different dot percent.

57. The multicolor volume hologram display unit of claim 53, characterized in that said multi-recorded volume holograms are each recorded in a separate pattern area.

25 58. The multicolor volume hologram display unit of claim 57, characterized in that an area swollen by said color tuning film and an unswollen area provide dots wherein red, green, and blue colors are reconstructible.

59. The multicolor volume hologram display unit of claim 58, characterized by including an area having a different dot area.

60. The multicolor volume hologram display unit of any
5 one of claims 53 to 59, characterized in that said color
tuning film is integrally provided thereon.

61. The multicolor volume hologram display unit of any one of claims 48 to 60, characterized by being used as a reflection hologram color filter.

ABSTRACT

5 The invention provides a diffusing plate with the angle of diffusion controllable within a desired range by use of a hologram, which is capable of presenting bright displays so that it is applicable to, for instance, a backlighting diffusing plate for liquid crystal display device. A diffusing plate 2 having an angle of diffusion θ is brought into close contact with a hologram photosensitive material 1. Then, parallel light 3 is obliquely at an angle of incidence α on the photosensitive material 1 while parallel light 4 is
10 vertically incident on the diffusing plate 2. Thereupon, parallel light 4 is converted into diffused light 5 having an angle of diffraction θ upon passing through the diffusing plate 2. Diffused light 5 interferes with obliquely incident parallel light 3 from the opposite direction in photo-
15 sensitive material 1 to produce interference fringes, thereby forming a reflection type hologram. Upon parallel illumination light on the hologram at the same angle of incidence α at which parallel light 3 strikes for recording, 20 diffused light having the same angle of diffraction θ as that of diffused light 5 used for recording is reflected, and diffracted from this reflection type hologram.

SECRET 071609

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10 (a)




FIG. 10 (b)




FIG. 11





FIG. 12



2025 RELEASE UNDER E.O. 14176






FIG. 14(a)




FIG. 14(b)




FIG. 14(c)




FIG. 15(a)




FIG. 15(b)




FIG. 16(a)




FIG. 16(b)




FIG. 17(a)





FIG. 17(b)








FIG. 19




FIG. 20(a)




FIG. 20(b)




FIG. 21(a)




FIG. 21(b)




FIG. 22




FIG. 23 (a)








FIG. 23(b)












FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG. 31 (a)




FIG. 31 (b)




FIG. 32 (a)




FIG. 32 (b)




FIG. 33






FIG. 34(a)



141 Red

FIG. 34(b)

Green




147 Dot

148 Background

142 Yellowish green

Yellow


FIG. 34(c)



143 Yellow

FIG. 34(d)

Red




147

148

144 Orange

Yellow

FIG. 34(e)



145 Green

FIG. 35




FIG. 36 (a)




FIG. 36 (b)




FIG. 36 (c)




Figure 6. The effect of the concentration of the polymer solution on the morphology of the films. The film was prepared by casting from a chloroform solution onto glass slides at room temperature. The thickness of the film was about 0.8 μm. The concentration of the polymer solution was 0.1 g/dl (A), 0.2 g/dl (B), 0.3 g/dl (C), 0.4 g/dl (D), 0.5 g/dl (E), 0.7 g/dl (F), 0.9 g/dl (G), 1.1 g/dl (H), 1.3 g/dl (I), 1.5 g/dl (J).




[illegible][illegible]

FIG. 38(a)




FIG. 38(b)




FIG. 39




FIG. 40(a)




FIG. 40(b)




FIG. 40(c)




FIG. 41(a)



FIG. 41(b)




FIG. 42(a)




FIG. 42(b)




FIG. 43




FIG. 44 (a)




FIG. 44 (b)




FIG. 44 (c)






FIG. 44 (d1)



66 Light irradiation

FIG. 44 (d2)



66 Light irradiation

FIG. 44 (d3)




FIG. 45(a)




FIG. 45(b)





FIG. 45(c1)


66 Light irradiation



65 Swelling film


FIG. 45(c2)

66 Light irradiation




65 Swelling film

FIG. 45(c3)




65 Swelling film

FIG. 45(d1)




64

FIG. 45(d2)



64


FIG. 45(d3)



64

United States Patent & Trademark Office

Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

1. Application papers are not suitable for scanning and are not in compliance with 37 CFR 1.52 because:
 - ☐ All sheets must be the same size and either A4 (21 cm x 29.7 cm) or 8-1/2" x 11".
Pages _____ do not meet these requirements.
 - ☐ Papers are not flexible, strong, smooth, non-shiny, durable, and white.
 - ☐ Papers are not typewritten or mechanically printed in permanent ink on one side.
 - ☐ Papers contain improper margins. Each sheet must have a left margin of at least 2.5 cm (1") and top, bottom and right margins of at least 2.0 cm (3/4").
 - ☐ Papers contain hand lettering.
2. Drawings are not in compliance and were not scanned because:
 - ☐ The drawings or copy of drawings are not suitable for electronic reproduction.
 - ☐ All drawings sheets are not the same size. Pages must be either A4 (21 cm x 29.7 cm) or 8-1/2" x 11".
 - ☐ Each sheet must include a top and left margin of at least 2.5 cm (1"), a right margin of at least 1.5 cm (9/16") and a bottom margin of at least 1.0 cm (3/8").
3. Page(s) _____ are not of sufficient clarity, contrast and quality for electronic reproduction.
4. Page(s) _____ are missing.
5. OTHER: NO Declaration